

DUP050106046

EST. WGT. ~~935~~ 935 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76

RETYPE BY
CJH 4/2/80

MAKING NOTES

REMARKS

TOTAL WGT 3332 #

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	244				
DATE	11/3/80				
TIME	8:30 AM				
RELEASED BY	OK				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	48	
PRESS WITH	AGITATION				
WASH TO 2000	OHMSWITH 35-75 F WATER				
TEST AFTER 2	HOURS				
LOAD ON 6 CARS					

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD	8124				
STARTED	51				
CAKES USED	732				
WATER ON	2				
HRS. WASHED	0500				
OHMS					
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	7				
NO. CARS LOADED					
EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY: #467 RELEASED BY:

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

No Record of any Processing Losses.

ADDITIONAL DRYING HOURS REQUIRED

**SAMPLES
DELIVER TO**

NO. CARS PULLED	
SAMPLED BY	

NO. DRUMS 13
LUMP WGT. 3217
RELEASED BY AL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN	RPM
MAX. TEMP.	OF

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING*
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

37
231
0

235
14
224
12
233
12
230
12
233
12
220
12
220
12
235
12
240
12
235
12
225
12
225
12
235
12
225
12
190
12
3219