
GT674 37508

30 2654 2426

[redacted] Lugano NP 2822

2654

N37403



DUP050041909

2264

CG 18 CODE GT-674-D PKG. ____

→ OCT 23 80 37508

EST. WGT. 2,800 ~~2300~~ LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	GT-674-D (Y)	AJC 01-16-78
		DCG 01-18-78
	TYPED BY	
	emw062979	

MAKING NOTES

REMARKS

NAME: MONASTRAL® GREEN B NON-BLEEDING

INSTRUCTIONS EC -PRESSING- RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT				264		STARTED	8 pm				
DATE				9-24		CAKES USED	6				
TIME				8 AM		HRS TO FILL					
RELEASED BY				8 AM		HRS. WASHED					
PRESS	15 & 16	17 & 18	9	9 & 10	10	OHMS					
NO. OF CAKES	4 x 42	4 x 42	2x76+16	7x76	x 43	HRS. WASHED					
PRESS with AGITATION						OHMS					
WASH TO OHMS						HRS. WASHED					
TEST AFTER HOURS						OHMS					
LOAD on 4 cars for 10, 15 & 16, 17 & 18						CAKE CONDITION					
on 5 cars for 9, 9 & 10						NO. CARS LOADED	6				
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

Dry 16 hrs at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 18

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 2872

SAMPLED BY RELEASED BY

-GRINDING-

MILL 7 or 8 HSP SCREEN 3/32" RPM 3560

MAX. TEMP. 210°F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

N37403.01

DUP050041910

37508
51
100

1.80	+
0.14	-
1.79	+
0.14	-
1.96	+
0.14	-
1.63	+
0.14	-
1.83	+
0.14	-
1.76	+
0.14	-
1.85	+
0.14	-
2.02	+
0.14	-
1.76	+
0.14	-
1.95	+
0.14	-
1.77	+
0.14	-
1.67	+
0.14	-
1.88	+
0.14	-
1.69	+
0.14	-
1.80	+
0.14	-
1.81	+
0.14	-
1.66	+
0.14	-
0.33	+
0.14	-
28.72	*
28.72	+

DUP050041911