

LOT L2H09

EST. WT. 5527* LBS.

ALTERNATE

COMTYP JOB NAME: 01YE698DPT

MAKING NOTES: _____

===== **EC** =====
= PRESSING =

INSTRUCTIONS				RECORD											
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 500 M MHOS WITH 35-75* WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
1245	10-28	10:45PM	MB	2	92	93				STARTED					
										CAKES USED					
										WATER ON					
										HRS. WASHED					
										M MHOS					
										HRS. WASHED					
										M MHOS					
										HRS. WASHED					
										M MHOS					
										CAKE CONDITION					
										NO CARS LOADED					
										EXPLAIN LOSSES					
SAMPLES 8 OZ.										SAMPLED BY					
DELIVER TO CTL.										RELEASED BY					

===== **EC** =====
= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F	LUMP: - OK - WET - SALTS - CONTAMINATD
(NOT EXTRUDED) DRY 10 HRS AT 240 F	
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLE	NO CARS PULLED
	NO DRUMS
	LUMP WGT
DELIVER	SAMPLED BY
	RELEASED BY

CO-GRIND PER CTL INSTRUCTIONS		GRINDING	
MILL MIKROATOMIZE	SCREEN	RPM	SCREEN
MAX. TEMP	DEG F		MAX. TEMP.
SET ROOF BLAST - GATE AT '5' FOR			
HIGH AIR FLOW			

EXPLAIN LOSSES

SAMPLE W/O MIXING	DATE MIXED
SAMPLES 1 ENV & 1 PINT CAN IF	
GROUND SEPARATELY	SAMPLED BY
DELIVER TO CTL	RELEASED BY