

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-788 LOT 34875

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>67</u>	<u>3,350</u>		

STUMP

TOTAL NET WT. 3,350 PKG. N-CODE 100

PROD. SPVR. WFF DATE 3/16/80 WHSE. OPER. _____

N 27525

22
1244 CO 03 CODE KY-788-D PKG.
MAR 14 34875
EST. WGT. 960 860 LBS.

O.K. BAGS
5460

OK.
HP

Total Wgt. 3560# Req()

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-788-D (J)	APPROVED BY ENK 9/22/76
	DCG 9/27/76
TYPED BY NE 2/17/77	
MAKING NOTES	

REMARKS

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	244	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3/14/80	STARTED	1:30 AM				
TIME	12:30 AM	CAKES USED	26				
RELEASED BY	CTK	WATER ON	3:30 PM				
PRESS	22	HRS. WASHED	5				
NO. OF CAKES	46	OHMS	2000				
PRESS WITH		HRS. WASHED					
WASH TO 2000		OHMS					
TEST AFTER 2		HRS. WASHED					
LOAD ON 6 CARS		OHMS					
		CAKE CONDITION	6				
		NO. CARS LOADED					
		EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR
DELIVER TO CIL for Color

SAMPLED BY 382 RELEASED BY

- DRYING -

Dry 12 hrs at 220 °F L.V.
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

No Drums 15
LUMP WGT. 3376
RELEASED BY

- GRINDING -

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 Env. & 1 Pt can
DELIVER TO CIL

DATE MIXED

SAMPLED BY

RELEASED BY

.00 T

.00 T

3 4 8.7 5 #

-4.1 #

.16 #

.00 T

2.45

.12 -

2.45

.12 -

2.40

.12 -

2.39

.12 -

2.42

.12 -

2.51

.12 -

2.52

.12 -

2.41

.12 -

2.45

.12 -

2.46

.12 -

2.49

.12 -

2.47

.12 -

2.35

.12 -

2.37

.12 -

1.42

.12 -

3 3.7 6 T