MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY 908 LOT 345024

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	71	3550		
	STUMP			

TOTAL NET WT. 3550 PKG. N–CODE 1138

PROD. SPVR.	DATE	WHSE. OPER.
JM	3/4/20	

N 27556

CG 03 CODE KY-908-D PKG. ____

→ FEB23 34502

EST. WGT. 949 LBS.

OK

KP

Total Wgt. 3549 #

PROCESSING INSTRUCTIONS: BATCH UNIT

22/240

PROCESSES	APPROVED BY
KY-908-D (E)	EWK 12/12/77
Alternate	DCG 12/14/77
TYPED BY	
rj 2/14/78	

MAKING NOTES

REMARKS

NAME: Krolor® Yellow - Light

NON-BLEEDING

INSTRUCTIONS –PRESSING– RECORD

						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
VAT		240				STARTED	1P				
DATE		2-23				CAKES USED	46				
TIME		11PM				WATER ON	5Am				
RELEASED BY						HRS. WASHED	5½				
PRESS	2	22	23	24		OHMS	2000				
NO. OF CAKES	46	46	46	52		HRS. WASHED					
PRESS with AGITATION						OHMS					
WASH TO 2000 OHMS with 135-145°F water						HRS. WASHED					
TEST AFTER 2 HOURS						OHMS					
LOAD on 6 cars						CAKE CONDITION	5				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8oz Jar

DELIVER TO Ctl for color

SAMPLED BY #38 RELEASED BY

–DRYING–

DRY 24 HOURS AT 180 °F

Dry on first stage only.
Reset every 5 hr til dry.

LUMP: – OK – WET – SALTS – CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 12

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3604

SAMPLED BY RELEASED BY

3/32

–GRINDING–

MILL939 HSP ~~1/8~~" RP SCREEN 3500 RPM

MAX. TEMP. 170 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 ENV & 1 PT CAN

DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050094771

N 27556.01

34502
4100
158

0.00 *

3.40 +
0.12 -
3.27 +
0.12 -
3.44 +
0.12 -
3.24 +
0.12 -
3.54 +
0.12 -
3.25 +
0.12 -
3.37 +
0.12 -
3.26 +
0.12 -
3.37 +
0.12 -
3.35 +
0.12 -
3.19 +
0.12 -
0.80 +
0.12 -
36.04 *

DUP050094772