MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 15x786 LOT E1316

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1790	1	T—	71	
1706	1	T—	141	
	STUMP	Large	3506	

TOTAL NET WT. 3496 PKG. N—CODE

PROD. SPVR. DATE WHSE. OPER.

5/21/17

9/22/76

CG 03 CODE KY-788-D PKG. ____

→ MAY -0-81- 21316

EST. WGT. 960 LBS.

3610

Total Wgt. 3560# Req( )

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

INSTRUCTIONS						-PRESSING- RECORD	1ST	2ND	3RD	4TH	5TH
VAT	244					PRESSLOAD STARTED	1 AM				
DATE	5-12-81					CAKES USED	54				
TIME	7 PM					WATER ON	4:30 AM				
RELEASED BY						HRS. WASHED	8				
PRESS	22	23	24			OHMS	200				
NO. OF CAKES	46	46	46			HRS. WASHED					
PRESS With		AGITATION				OHMS					
WASH TO 2000		OHMS with 35-75°F water				HRS. WASHED					
TEST AFTER	2	HOURS				OHMS					
LOAD on 6 cars						CAKE CONDITION					
		6 Cars				NO. CARS LOADED	6 → 2				
						EXPLAIN LOSSES					

SAMPLES 1- 8oz JAR

DELIVER TO CTL for Color

SAMPLED BY BHe RELEASED BY BHe

-DRYING-

Dry 12 hrs at 220 °F

Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

No Drums 16

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3506

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096410

1316
41
158

2.33 +
0.14 -
2.56 +
0.14 -
2.41 +
0.14 -
2.39 +
0.14 -
2.31 +
0.14 -
2.25 +
0.14 -
2.38 +
0.14 -
2.35 +
0.14 -
2.38 +
0.14 -
2.38 +
0.14 -
2.31 +
0.14 -
2.23 +
0.14 -
1.60 +
0.14 -
28.06 *

1316
41
100

28.06 +
2.60 +
0.12 -
2.40 +
0.12 -
2.36 +
0.12 -
35.06 *

DUP050096411