

S.V.

C.V.

D.V.

CG 20
JUN 18 1982

CODE BT

12K85

PKG

PROCESSES

() BT-417-D (M)

APPROVED BY
BBK 1/14/82

(DATE)

(LOT NUMBER)

(SIGNED)

(DATE)

EST. WT. 2517* LBS.

TYPED BY: DAJ/ATA
STANDARD HRS.

TIME _____ M

USE +/- 2600# N-8710-A

PREPARATION NOTES:

EQUIP
MENT

NAME: MONASTRAL BLUE GF

1 PAGE

USE
LBS

N-CODE

ACCT
LBS~~LOAD~~

LOT

±100%

%

8710-A

CALCULATE EST. WT.:

÷ N8710 X .969 = ÷ EST. WT.

RECORD EST. WT. ON MAKE & PROCESS CARDS

N-7368

N38159

PRODUCT NAME = MONASTRAL BLUE GF

DATE PRINTED: 4/02/82

CG 20 CODE BT-417-D PKG ____

PROCESSES | APPROVED BY
BT-417-D (M) | BBK 1/14/82
TYPED BY: DAJ

JUN 18 1982

F2K85

(DATE)

(LOT)

NOTES: _____

EST.WT. 2517* LBS.

JOB NAME: 20BT417DPM

INSTRUCTIONS

= PRESSING =

RECORD

Lump to Press
~~PALEONT~~

= DRYING =

DRY 20 HOURS AT 220°F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MILL 7 OR BLSP 1/8" SCREEN 1785 RPM
MAX. TEMP 140 DEG F
INERT MILL WITH CO2 WHEN GRINDING
PER OP #0043.

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 2 PT CANS
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050047744