

CO 03 CODE KY-787-D PKG.

→ JAA 13 33797
EST. WGT. ~~2230~~ 1980 LBS.

PROCESSES	APPROVED BY
KY-787-D (S)	EWK 10-19-77
Alternate	DCG 10-25-77
TYPED BY -	
JIC 11-4-77	
MAKING NOTES	

REMARKS

TOTAL WGT ~~2230~~ (REQ)

NAME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT	262			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-15-80			STARTED					
TIME	8:45			CAKES USED					
RELEASED BY				WATER ON					
PRESS	96	96	89.5	HRS. WASHED					
NO. OF CAKES	10	72	84	OHMS					
PRESS WITH				HRS. WASHED					
WASH TO	2000			OHMS					
TEST AFTER	4			HRS. WASHED					
LOAD ON 10 CARS				OHMS					
				CAKE CONDITION					
				NO. CARS LOADED	12				
				EXPLAIN LOSSES					

SAMPLES 1-8 oz. JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY 472 RELEASED BY

-DRYING-

HOURS DRY 12 HRS AT 220°F.
TEMP. THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNo. Drums: 30
LUMP WGT. 71.83
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE A WITHOUT MIXING

DATE MIXED

SAMPLES 1 env + 1 Pt Can

DELIVER TO CTL

SAMPLED BY

RELEASED BY

65 22

252

41

33797

33797
41
252

6

7