

1.56
1.47
1.54
1.54
1.65
1.73
1.53
1.53
1.55
1.63
1.50
1.62
1.57
1.53
1.60
2.25
2.49 T

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE 14-808-0 LOT 93730

NET WT/PKG NO. PKG PACK. WGT LOCATION PO

17 2495 11-8

14-2494 **STUMP**

TOTAL NET WT. 2495 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

RY 11/13/90 74

DUP050293370

N33123.01

PROCESSING INSTRUCTIONS: BATCH UNIT

CO 45 CODE YT-808-D PKG.

JAN 10 33730
EST. WGT. 2573 LBS.

PROCESSES	APPROVED BY
YT-808-D (D)	ENK 9/28/77
	BBK 10/17/77
	DCG 10/17/77
TYPED BY	
JTC 10/26/77	
MAKING NOTES	

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE					STARTED	5 PM				
IME					CAKES USED	68				
RELEASED BY					WATER ON	7:30				
RESS	32	33	35		HRS. WASHED	4				
O. OF CAKES	60	62	60		OHMS	5000				
RESS	WITHOUT AGITATION				HRS. WASHED					
ASH TO	4000	OHMS with 35-75°F water			OHMS					
EST AFTER	4	HOURS			HRS. WASHED					
DAD	on 9 cars				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	247				
					EXPLAIN LOSSES					

AMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 200°F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

AMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

NO. DRUMS

LUMP WGT.

RELEASED BY

-GRINDING-

 ALL 4 OF 10 HSP 1/8" R3 SCREEN 3500 RPM
 MAX. TEMP. 100 °F

 SCREEN RPM
 MAX. TEMP. °F

EXPLAIN LOSSES

AMPLE WITHOUT MIXING

AMPLES 1 env + 1 Pint can

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050293371

N33123.02

33730
51
252

0.00 *
1.63 +
0.12 -
1.57 +
0.12 -
1.52 +
0.12 -
1.60 +
0.12 -
1.60 +
0.12 -
1.80 +
0.17 -
1.79 +
0.17 -
1.63 +
0.12 -
1.72 +
0.17 -
1.70 +
0.17 -
1.61 +
0.12 -
1.66 +
0.12 -
1.71 +
0.17 -
1.65 +
0.12 -
1.66 +
0.17 -
1.58 +
0.12 -
0.85 +
0.12 -
24.94 *