

Bigelow-Liptak

G-18

INSULATING CEMENT

For Industrial Furnaces

An all-purpose rust inhibitive insulating cement for temperatures up to 1800° F.

Net Weight 50 lbs.

IMPORTANT INSTRUCTIONS

1. Remove all dust, dirt, grease and paint from surface to be insulated.
2. Mix contents of this bag (50 lbs.) with 12 gallons of clean, fresh water.
3. Provide heat in equipment, if possible, to accelerate drying.
4. Apply first coat by "spotting" on to a thickness of $\frac{3}{4}$ " to 1" and allow to set-up.
5. Apply additional coats as required, allowing each coat to set-up before applying next.
6. Trowel last coat to a smooth, even finish when required thickness is obtained.
7. Caution! allow Bigelow-Liptak insulating cement to dry thoroughly before applying finishing cement or WP Protective coating.

BIGELOW-LIPTAK CORPORATION
13300 PURITAN AVE. • DETROIT 27, MICHIGAN

CAUTION: This product contains asbestos fibers. Inhalation of asbestos in excessive quantities over long periods of time may be harmful. If dust is created when this product is handled, avoid breathing the dust. If adequate ventilation control is not possible, wear respirators approved by the U.S. Bureau of Mines for pneumoconiosis producing dust.