

CODE 1710 LOT 2116

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

2200

1

7-

93

2110

1

7-

285

STUMP

Lump

44-35

4,310

TOTAL NET WT.

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JW

514187

270

CG 03 CODE KY-781-D

PKG.

MAY - 0-81 - E1163

EST. WGT.

1428 LBS.

OR
H

4/24

Grind Shop

Grind and Packout on tickets
and packages as lot D 1163 not E 1163

Total Wgt. 4428#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-781-D (N)

APPROVED BY
FWP 10-13-78

AMJ 10-13-78

TYPED BY

emw101378

MAKING NOTES

REMARKS

NAME: KROLO® YELLOW LIGHT

NON-BLEEDING

INSTRUCTIONS						- PRESSING -		RECORD				
VAT	240					PRESSLOAD		1ST	2ND	3RD	4TH	5TH
DATE	4-29-81					ST/RYED		4 PM				
TIME	1:20 PM					CAKES USED		46				
RELEASED BY	C.M.					WATER ON		8 PM				
PRESS	2	22	23	24		HRS. W/ SHED		14				
NO. OF CAKES	46	46	46	52		OHMS		5000				
PRESS	With AGITATION					HRS. W/ SHED						
WASH TO	5000	OHMS with 35-75°F water				OHMS						
TEST AFTER	4	HOURS				HRS. WASHED						
LOAD	on 6 cars					OHMS						
						CAKE CONDITION						
						NO. CARS LOADED		6				
						EXPLAIN LOSSES						

SAMPLES 1-8 oz jar
DELIVER TO CTL FOR COLOR

SAMPLED BY

RELEASED BY

VW

- DRYING -

DRY 16 HOURS AT 220 °F LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 16
LUMP WGT. 4433
RELEASED BY

- GRINDING -

MILL 939 HSP 3/4" RP SCREEN 3500 RPM
MAX. TEMP. 210°F

SCREEN RPM
MAX. TEMP.

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO CTL

DATE MIXED
SAMPLED BY

RELEASED BY

E1063

305

0.00 *

2.88 +
0.12 -/
2.97 +
0.12 -/
2.89 +
0.12 -/
2.84 +
0.12 -/
2.93 +
0.12 -/
2.99 +
0.12 -/
3.05 +
0.12 -/
2.84 +
0.12 -/
3.00 +
0.12 -/
25.31 *

3.31 +
3.01 +
0.12 -/
2.96 +
0.12 -/
2.67 +
0.14 -/
2.91 +
0.12 -/
3.01 +
0.12 -/
2.78 +
0.12 -/
2.56 +
0.12 -/
44.35 *

E 1163