

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

K0-906

LOT

K2H28

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

2450

1

T.

86

2410

1

T.

17

STUMP

K0-906

TOTAL NET WT.

4860

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JH

10/21

PRODUCT NAME = KROLOR ORANGE - R (NON-BLEEDING)

DATE PRINTED: 2/03/82

CG 04 CODE KO-906-D PKG

PROCESS

APPROVED BY

SEP 28 1982

K2H28

KO-906-D (C)

FWP 12/10/81

DATE

LOT NUMBER

MAKING NOTES

EST. WT. 5000* LBS.

JOB NAME: 04K0906DPC

INSTRUCTIONS					PRESSING		RECORD				
VAT					246	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE					9-30	STARTED	4 PM				
TIME					21:15	CAKES USED	48				
RELEASED BY					93	WATER ON	18				
PRESS	22	23	24	25		HRS. WASHED	12				
NO. OF CAKES	46	46	52	48		OHMS					
PRESS WITH						HRS. WASHED					
WASH TO 2000 OHMS						OHMS					
TEST AFTER 3 HOURS						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION	7				
						NO CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES
DELIVER TOSAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F

NOTE: DRY ON FIRST STAGE ONLY.

RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATED

*cannot account for low yield.
No record of any process time.*

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 8 OZ. JAR
DELIVER TO CTL

NO CARS PULLED

NO DRUMS
LUMP WGT

SAMPLED BY

RELEASED BY

= GRINDING =

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN

RPM

MAX. TEMP.

F

SAMPLE W/O MIXING 1 ENV & 2 PT CANS
IF PACKED IN BAGS SAMPLE AS FOLLOWS:
FIRST BAG: 1 ENV.
40TH BAG: 1 ENV. & 2 PINT CANS
LAST BAG: 1 ENV.
DELIVER TO CTLEXPLAIN LOSSES
EXPLAIN LOSSES

DATE MIXED

SAMPLED BY
RELEASED BY

28
41
85

0.00 *

0.00 *

3.05 + -

0.12 -

2.95 + -

0.12 -

3.08 + -

0.12 -

3.14 + -

0.12 -

3.06 + -

0.12 -

2.88 + -

1.22 -

3.03 + -

0.12 -

2.78 + -

0.12 -

2.89 + -

0.12 -

2.87 + -

0.12 -

2.87 + -

0.12 -

3.01 + -

0.12 -

3.09 + -

0.12 -

2.79 + -

0.12 -

2.93 + -

0.12 -

3.18 + -

0.12 -

3.02 + -

1.22 -

1.32 + -

0.12 -

47.56 *

181