MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KO 789 LOT 33801

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2584	1	T. 250		

STUMP

TOTAL NET WT. 2584 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

1/19/80

24
245

CG 04 CODE KO-789-D PKG. ____
→ JAN 14 33801
EST. WGT. ~~1199~~ 509 LBS.

OK
AP

2609

Total Weight ~~5199#~~ (Req. _____)

PROCESSING INSTRUCTIONS: BATCH UNI

PROCESSES	APPROVED B
KO-789-D (I)	EWK 9-21-7
	DCG 9-21-7
	MTW 10-2-7
TYPED BY	
jlc 10-8-76	

MAKING NOTES

REMARKS

NAME: "KROLOR" ORANGE Y

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT	245				
DATE	1-16				
TIME	530A				
RELEASED BY	JDC				
PRESS	22	23	24	25	
NO. OF CAKES	46	46	52	~~48~~ 24	

PRESS with AGITATION
WASH TO 5000 OHMS with 35-75°F water
TEST AFTER 6 HOURS
LOAD on ~~6~~ 3 cars

SAMPLES 1 - 8 oz. jar
DELIVER TO CTL for color

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	ST
STARTED	530AM				
CAKES USED	26				
WATER ON	8 AM				
HRS. WASHED	9				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	3				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY TDS

-DRYING-

DRY 16 HOURS AT 220°F L.V. H.V.
TEMP. °F °F

LUMP: - OK - WET - SALTS - CONTAMINAT

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS: 9

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 2623
SAMPLED BY RELEASED BY Ger

-GRINDING-

MILL 938 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 210 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env. + 1 Pint Can
DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050095370

33801
4100
17

DUP050095371