CODE Ky-181 LOT 81199

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2698	1	T: 274		
1734	1	T: 187		
	STUMP	Lump 4392		

TOTAL NET WT. 4432 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

5,2,81

23
244

CG 03 CODE KY-781-D PKG.

MAY ~~ERR~~-0-81 D 1199

EST. WGT. 1128 LBS.

4/24

Grind Shup
Grind + Packout as D 1199

Total Wgt. 4428#

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-781-D (N)	FWP 10-13-78
	AMJ 10-13-78
TYPED BY	
emw101378	

MAKING NOTES

REMARKS Mark your packages as lot D1199

NAME: KROLOR® YELLOW LIGHT NON-BLEEDING

-PRESSING- INSTRUCTIONS

DAY	244				
DATE	4-25-81	(SAM)			
TIME	510 AM				
RELEASED BY	JJ				
PRESS	2	22	(23)	24	
NO. OF CAKES	46	46	46	52	

PRESS with AGITATION
WASH TO 5000 OHMS with 35-75°F water
TEST AFTER 4 HOURS
LOAD on 6 cars

SAMPLES 1 - 8 oz Jar
DELIVER TO CTL for color

-PRESSING- RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8-Pm				
CAKES USED	46				
WATER ON	7-PM				
HRS. W/ SHED	16				
OHMS	5100				
HRS. W/SHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

DRY 16 HOURS AT 220 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES
DELIVER TO

NO. CARS PULLED LUMP WGT. 4392

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 210°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLES WITHOUT MIXING
SAMPLES 1 Env & 1 Pt
DELIVER TO CTL

DATE MIXED

SAMPLED BY RELEASED BY

DUP050096216

1199
41
17

0.00 *

3.33 +
0.12 -
3.49 +
0.12 -
3.03 +
0.12 -
3.34 +
0.12 -
3.35 +
0.12 -
3.21 +
0.12 -
3.17 +
0.12 -
3.01 +
0.12 -
3.35 +
0.12 -
3.23 +
0.12 -
3.36 +
0.12 -
3.34 +
0.12 -
3.09 +
0.12 -
3.30 +
0.12 -
43.92 *

DUP050096217