

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE YC-10-B LOT A2K27

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

<u>50</u>	<u>120</u>	<u>6.000</u>		

~~STAMP~~

63416

TOTAL NET WT. 6.000 PKG. N-CODE 1000

PROD. SPVR.

DATE

WHSE. OPER.

84 112382

PRODUCT NAME = MOLYBDATE ORANGE

NON-BLEEDING

1/15/82

CG 01 CODE YC-010-B PKG

PROCESSES APPROVED BY
YC-010-B (G) FWP 10/09/81
ALTERNATE
TYPED BY JMH

LOT A2K27

EST. WT. 5575* LBS.

MAKING NOTES

JOB NAME: 01YC010BPG

INSTRUCTIONS				= PRESSING =	RECORD									
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF Cakes	WASH TO 500 M MHDS WITH 35-75% WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
				2	54	92	93	54	STARTED	4:40 PM				
									CAKES USED	54				
									WATER ON	7:50 PM				
									HRS. WASHED	2				
									M MHDS	250				
									HRS. WASHED					
									M MHDS					
									HRS. WASHED					
									M MHDS					
									CAKE CONDITION					
									NO CARS LOADED	6				
									EXPLAIN LOSSES					

SAMPLES
DELIVER TOSAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

Color appears dry
Extruded
ADDITIONAL DRYING HOURS REQUIREDSAMPLES
DELIVER TONO CARS PULLED
SAMPLED BY
RELEASED BYNO DRUMS 22
LUMP WGT 6346

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOWSCREEN RPM
MAX. TEMP F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV.
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050109501