Thermo Electron
EAL Corporation

2030 Wright Avenue
Richmond, California 94804
(415) 235-2633
(TWX) 910-382-8132

PLAINTIFF'S EXHIBIT
CHV-823

ANALYSIS REPORT

CHEVRON CORPORATION
P.O. BOX 7924
SAN FRANCISCO, CA 94120-7924
ATTN: R.J. REINHART

DATE: 6-12-86
Samples Received: 6-2-86
EAL W.O. No. 17994-0
Purchase Order No. CWPR S-69815-
Batch No. LRL 86-3

SAMPLE IDENTIFICATION		~~ASBESTOS~~ Ceramic FIBER COUNT		VOLUME
EAL	CUSTOMER	fibers/filter	fibers/cc	(liter)
37-936-1	AA 22512	2500.	0.0078	324.
37-936-2	AA 22639	640000.	5.8	109.2
37-936-3	AA 22640	500000.	4.6	108.
37-936-4	AA 22578	2000.	0.0032	630.
37-936-5	AA 22579	2000.	0.0030	662.4
37-936-6	AA 22638	<1000.	--	--

Analysis by phase contrast microscopy per NIOSH P&CAM 239

SAMPLE IDENTIFICATION		QUARTZ	CRISTOBALITE	TRIDYMITE
EAL	CUSTOMER	%	%	%
37-936-7	BULK 1	5	1	<1

Analysis by x-ray diffraction

Fiber diameter estimates: #22639 range = <0.5 to 10 um, average = 3 um
22640 range = <0.5 to 8 um, average = 3 um.

Jesse E. Fisher
Program Manager

EAL Corporation laboratories are Accredited by the American Industrial Hygiene Association; approved by the State of California for complete chemical, radiological, bacteriological, and bioassay analyses.