Manville

160-65

Manville Research
November 3, 1948

File 45751-48a

G. H. Schlammer - Waukegan

Manufacturing Specifications
24-B Acid Resistant Sheet Packing
Your letter to Mr. C. La Gattuta, October 25th.

We have reviewed, and are in accord with, the proposed changes in formula and mixing procedure for the manufacture of standard Style 24-B compressed asbestos sheet packing covered by your above letter. However, we would like to point out at this time that the blue fiber we have been purchasing from the Asbestos Company of America is a blend of blue fiber rather than straight Australian blue fiber. Therefore, it is suggested that the Australian blue fiber in the proposed formula be changed to "Blended Blue Asbestos Fiber (Crocidolite)".

The quantity of sulphur shown in your above letter under present specification should be 2 pounds 15 ounces rather than 1 pound 15 ounces. Also, under the present mixing procedure, the mixing time should be 20 minutes instead of 2 minutes.

H. J. Columbo

cm

E. R. Williams
R. T. Halstead
H. C. Koch
E. C. Lindstrom, CH
C. La Gattuta, DHQ
E. A. Jaeschke, Waukegan
H. C. Howe, Waukegan

PLAINTIFF'S EXHIBIT WV-04579

PLAINTIFF'S EXHIBIT 10866.0