

FOLDER w/NO NAME

5-25-88

Bob,

Could you get 1st Samples of PVC from

- ① Shulman - Polyvan 7929 - ^{Sample} request 6/20
- ② Standard - MS 4609-80 NO

Material is for Chrysler Quote for CKR.

6/30
Greg Lyburne to talk to skip about problem with
material spec.

Skip

Bob

any Luck finding these

Jim Carman is pushing

Skip

Chrysler

CHARDO 02030

5-25-88

Bob,

Could you get 1st Samples of PVC from

① Shulman - Polyvan 7929

② Standard - MS 4609-80

Material is for Chrysler Quote for CKR.

Shy

HARDNESS 70+/-5

STOCK NO. 03274

CKR EXP.SHULM.-275

COMPOUNDED BY

03/20/90

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	100.00	71.94	52.35	200.00
017	MERROL E-68	3.00	3.03	1.57	6.00
030	VICRON 15-15	15.00	5.56	7.85	30.00
053	STEARIC ACID DP	.50	.63	.26	1.00
146	SYNPRON 1530	2.50	2.40	1.30	5.00
006	DINP	70.00	70.71	36.64	140.00 A

TOTAL	191.00	154.27	99.99	382.00
-------	--------	--------	-------	--------

.48	-	PHYSICAL PROPERTIES
USE	-	SPEC. MIN. MAX.
REPLACES	-	SPECIFIC GR. 1.238
REASON	-	HARDNESS
COLOR	-	TENSILE
REQUIRMENTS TO MEET	-	ELONGATION
	-	MODULUS @
	-	MOONEY @
	-	SCORCH
	-	CURE

LAB	-
COST	-
MIXING	-

STOCK CONTROL TEST

CHARDO 02032