

(DRY AND PASTE ONLY)

36078

PQ

4

266

Page 4474

PKG. N-CODE

WHSE. OPER.

61415-0

DI 1005045000

23
240

CG 03 CODE KY-795-D PKG.

→ JUN-11 36079
EST. WGT. 1178 880 LBS.

TOTES
PER LAB
OK
HP

Total Wgt: 4678# 4380

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
KY-795-D (I)
Alternate

APPROVED BY
EWK 10/6/76
DCG 10/7/76

TYPED BY
NE 3/3/77

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	6-12-80					STARTED	10:00 AM				
TIME	11:15 AM					CAKES USED	46				
RELEASED BY	H. G.					WATER ON	9:30				
PRESS	22	23	24			HRS. WASHED	14 1/2				
NO. OF CAKES	46	46	46	52		OHMS	10000				
PRESS with						HRS. WASHED					
WASH TO	5000					OHMS					
TEST AFTER	5					HRS. WASHED					
LOAD	on 5 cars					OHMS					

ARK

SAMPLES 1-8 oz JAR
DELIVER TO Ctl TOP COLOR

SAMPLED BY #469

RELEASED BY J.K.

-DRYING-

Dry 16 Hrs. at 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

No Drums: 13
LUMP WGT. 4474
RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 210 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 Env & 1 Pt Can
DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY

N32142.01

30079
209
12

0.00 *
0.00H+
3.19 +
0.12 -
3.43 +
0.12 -
3.37 +
0.12 -
3.62 +
0.12 -
3.54 +
0.12 -
3.48 +
0.12 -
3.43 +
0.12 -
3.72 +
0.12 -
3.55 +
0.12 -
3.65 +
0.12 -
4.01 +
0.12 -
3.42 +
0.12 -
3.90 +
0.12 -
44.74 *
44.74H+

N32142.02

DUP050456805