

Specifications

New White HI-LITE Acoustical Plaster *stipple or stipple-perforated finish*

MIXING—Machine mixing is required. Do not retemper or mix one batch with another. Keep all tools and equipment clean. Mix no more than can be used in one hour.

HI-LITE Acoustical Plaster Basecoat: Use approximately 34 quarts of water per bag. Add HI-LITE Basecoat to water and mix until mortar weighs 15 to 17 lbs. net per 12 qt. pail. (Approximately 10 to 15 minutes depending on speed of mixer.)

HI-LITE Acoustical Plaster Finish Coat: Use approximately 32 quarts of water per bag. Add HI-LITE Finish Coat to water and mix until mortar weighs 15 to 17 lbs. net per 12 qt. pail. (Approximately 6 to 12 minutes depending on speed of mixer.)

APPLICATION—HI-LITE Acoustical Plaster shall be applied in two coats to a uniform total thickness of $\frac{1}{2}$ " over a basecoat of RED TOP® Gypsum Plaster. A full scratch and brown coat that has been cross-raked is required over metal lath, ROCKLATH® Plaster Base and masonry bases (not monolithic concrete) to provide proper rigidity, strength, and a solid base for the acoustical plaster.

HI-LITE Acoustical Plaster (*Sound absorption data*)

	Thickness	Frequency							Authority
		128	256	512	1024	2048	4096	NRC	
Stippled	$\frac{1}{2}$ "	.22	.25	.47	.72	.78	.80	.55	Nat'l Bur. of S.
Stipple-Perforated	$\frac{1}{2}$ "	.20	.24	.48	.77	.84	.86	.60	Nat'l Bur. of S'tds.

	Thickness	Frequency							Authority
		125	250	500	1000	2000	4000	NRC	
Stipple-Perforated	$\frac{1}{2}$ "	.20	.24	.50	.76	.83	.76	.60	Riverbank Laboratory

Direct application of HI-LITE Acoustical Plaster to existing ceilings or concrete

HI-LITE may be applied over existing plaster and over new or existing smooth concrete ceiling with the use of asphalt emulsion (Type N-13 HPC or C-13 HPC) as a bonding agent.

On existing painted plaster or concrete ceilings, the surface must be dry, clean and sound. Calcimine or similar powder paints must be washed off and wax, grease or oil removed. Loose or improperly bonded plaster or paint must be removed and such areas repaired with wood fiber or patching plaster. Allow patches to dry 2 or 3 days. On new concrete ceilings which are smooth, level, and dense, surface must be dry, free of dust, oil, grease, or efflorescence.

Size any porous concrete, or porous or unpainted plaster surface with cut-back asphalt, shellac, or varnish to reduce suction before asphalt emulsion is applied.

Trowel on asphalt emulsion in thin coat not to exceed $\frac{1}{16}$ " thick. Cover entire ceiling area. The first $\frac{3}{8}$ " of HI-LITE should follow application of the emulsion as closely as possible and while the emulsion is still soft and plastic.

Darby first coat of HI-LITE to a true even surface with a minimum amount of pressure. Allow to set and partially dry. Apply HI-LITE finish coat as specified.

Application of HI-LITE Acoustical Plaster over monolithic concrete surfaces

Over properly prepared rough monolithic concrete surface apply BONICRETE® plaster according to directions and not to exceed $\frac{1}{4}$ " thickness on ceilings nor

$\frac{3}{4}$ " on side walls. Apply the HI-LITE over the set, partially dry BONICRETE basecoat, as specified above.

Directions for painting HI-LITE Acoustical Plaster

Remove all loose dirt or dust from HI-LITE by use of a vacuum cleaner with hose and brush attachment.

Paint: Should be water-thinned. TEXOLITE® Imperial is recommended. First coat—mix one part TEXOLITE paste to one part water by volume. Second coat if required—mix one part TEXOLITE paste to two parts water by volume.

Spray on with any gun with a medium fine spray. DeVilbiss spray gun, type M3D, with a No. 30

nozzle or equivalent is recommended. Use 30 to 40 lbs. pressure in the gun and 20 to 30 lbs. on the paint.

Hold nozzle 14 to 18 in. away from work. Use a slow, uniform motion. Cover surface in one pass. Do not pass over same area several times as this builds up paint unnecessarily.

Allow at least overnight drying between coats. If weather is extremely humid, allow additional drying as necessary.

Copyright 1953, United States Gypsum Co.

*T. M. Reg. U. S. Pat. Off.



UNITED STATES GYPSUM

The Greatest Name in Building

PLAINTIFF'S EXHIBIT

USG-1439

GP040 1224