

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE K7 787 LOT 33825

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
<u>50</u>	<u>66</u>	<u>3,300</u>		

STUMP

TOTAL NET WT. 3,300 PKG. N-CODE 1139

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

JMT 1/20/80

23/44
244

CG 03 CODE KY-787-D PKG. _____
→ JAN 15 33825
EST. WGT. 1090 LBS.

OK
R

OK
BAGS

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	KY-787-D (R)	FWK 9/22/76
	Alternate	DCG 9/27/76
	TYPED BY	
	NE 2/12/77	
MAKING NOTES		
REMARKS		

Total Wgt. 3490#

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
VAT		244			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		1-16			STARTED	4:30				
TIME		12:00			CAKES USED	410				
RELEASED BY		SA			WATER ON	10:45 AM				
PRESS	22	23	24	24	HRS. WASHED	3 1/2				
NO. OF CAKES	46	46	46	52	OHMS	3000				
PRESS with		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION	5				
					NO. CARS LOADED	5				
					EXPLAIN LOSSES					

FDS

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY RELEASED BY FDS

-DRYING-

Dry 12 hrs at 220°F.	LUMP: - OK - WET - SALTS - CONTAMINATED
Then Dry 8 hrs at 160°F.	
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	No. Drums 13
DELIVER TO	NO. CARS PULLED LUMP WGT. 3322
	SAMPLED BY RELEASED BY JCG

-GRINDING-

MILL 939 HSP 3/32" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 150 °F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING	DATE MIXED		
SAMPLES 1 ENV & 1 Pt. can			
DELIVER TO C T L	SAMPLED BY	RELEASED BY	

DUP050093285

N 26183.01

33825
4100
17

3

2

2

2

2

2

3

2

2

2

2

2

6

3 37