ENAMELOID, SAGE GREEN

CONTENTS OF CAN:
Pigment by weight..... 46%
Liquid by weight..... 54%
100%

The Liquid is Varnish.

COMPOSITION OF PIGMENT:
Zinc Oxide..... 91%
*Color..... 9%
100%

*COLORING MATERIAL:
Umber
10% Manganese Oxide
45% Ferric Oxide
45% Silica and Silicates
Chromium Green
17% Lead Chromate
5% Lead Sulphate
80% Barium Sulphate
8% Kaolin
46 Ferric Ferro Cyanide
Chrome Yellow
65% Lead Chromate
35% Lead Sulphate

R725

ENAMELOID

AN ENAMEL FINISH — FOR INSIDE USE

HALF GALLON
U. S. STANDARD MEASURE



SAGE GREEN

THE SHERWIN-WILLIAMS CO.
PAINT AND VARNISH MAKERS
FACTORIES: CLEVELAND, CHICAGO, NEWARK, MONTREAL, LONDON, ENG
SALES OFFICES AND WAREHOUSES IN PRINCIPAL CITIES.

DIRECTIONS—Stir thoroughly from bottom of can. Be sure that the surface is dry and free from grease and dirt. Apply in full, even coats with a soft bristle brush. If necessary, thin with a little pure spirits of turpentine only. Allow 24 hours between coats.
U218 L10 453
MADE IN U. S. A.

DIRECTIONS—Stir thoroughly from bottom of can. Be sure that the surface is dry and free from grease and dirt. Apply in full, even coats with a soft bristle brush. If necessary, thin with a little pure spirits of turpentine only. Allow 24 hours between coats.
U218 09 1008
MADE IN U. S. A.

DIRECTIONS—Stir thoroughly from bottom of can. Be sure that the surface is dry and free from grease and dirt. Apply in full, even coats with a soft bristle brush. If necessary, thin with a little pure spirits of turpentine only. Allow 24 hours between coats.
U218 09 1008
MADE IN U. S. A.

ENAMELOID, BLACK

Pigment by weight..... 3%
Liquid by weight..... 97%
100%

The Liquid is Varnish
The Pigment is Carbon.

R729

ENAMELOID

AN ENAMEL FINISH — FOR INSIDE USE

HALF GALLON
U. S. STANDARD MEASURE



BLACK

THE SHERWIN-WILLIAMS CO.
PAINT AND VARNISH MAKERS
FACTORIES: CLEVELAND, CHICAGO, NEWARK, MONTREAL, LONDON, ENG
SALES OFFICES AND WAREHOUSES IN PRINCIPAL CITIES.

DIRECTIONS—Stir thoroughly from bottom of can. Be sure that the surface is dry and free from grease and dirt. Apply in full, even coats with a soft bristle brush. If necessary, thin with a little pure spirits of turpentine only. Allow 24 hours between coats.
U218 L10 453
MADE IN U. S. A.