

CG 01 CODE YE-698-D PKG

92
42

LOT

MAY -0-81-E 1499

013

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

APPROVED BY
YE-698-D (R) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPR

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 91 92 93
NO.OF CAKES 32 42 32 32
PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

1ST	2ND	3RD	4TH	5TH
PRESSLOAD				
STARTED				
CAKES USED				
WATER ON				
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
HRS. WASHED				
OHMS				
CAKE CONDITION				
NO CARS LOADED	4			
EXPLAIN LOSSES				

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY
NO DRUMS 17
LUMP WGT 3439

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT '9" FOR HIGH
AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1499
41
85

3.59 +
0.14 -
3.50 +
0.14 -
3.36 +
0.14 -
3.25 +
0.14 -
3.39 +
0.14 -
3.52 +
0.14 -
3.16 +
0.14 -
3.51 +
0.14 -
3.23 +
0.14 -
3.46 +
0.14 -
1.96 +
0.14 -
34.39 *