

VISCOSITY WORK SHEET

Item 464-468	P.T.No.	Date 1/13/56
Worker Stanley	Polymer Lucite	Solvent CCl ₄
For Cameron	Charge 1329	Temperature 20°C
Viscometer No. 117	Efflux Time 152.0; 151.9	Weight: Gross 3.6084
Viscometer No. C	Efflux Time 167.9; 162.9	Tare 3.4834
Viscometer No. 8	Efflux Time 159.6; 159.6	Net 0.1250
A	70.3; 170.2	

Sample	Flask	No.	Visc.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.
5146-27C	BB	III	189.3; 179.3		1.244	0.44
5146-27D	DZ	C	209.2; 209.2; 209.2		1.245	0.44
5146-28A	10	8	203.4; 203.3; 203.2		1.274	0.48
5146-28B	H5	A	217.0; 217.1; 217.1		1.274	0.48
5146-28C	14	III	193.0; 193.1; 193.2		1.271	0.48
5146-28D	13	C	213.8; 213.8		1.273	0.48

PC-1

1-13:56
mcy

N38879