PLAINTIFF'S
EXHIBIT NO. P-14
FOR IDENTIFICATION
DATE: 3/29/95 RPTR: BK

1615 TALC (B.C.)*

Typical Chemical Analysis:

			Percent
Silica	SiO_2		58-62
Calcium Oxide	CaO		0.6-1.2
Aluminum Oxide	Al_2O_3		2-4
Magnesium Oxide	MgO		29-31
Moisture		not more than	0.5
Loss on Ignition		not more than	7
Water Solubles		not more than	0.1
Acid Solubles		not more than	6
Water Soluble Iron			None
pH			9-10

Typical Physical Properties:

Dry Brightness	85-90
Specific Gravity	2.68
Tapped Density, lbs./cu.ft.	56-60
Loose Density, lbs./cu.ft.	[illegible]4-29
Lbs./solid gallon	22.32
One Lb. Bulks, gallons	0.0448
Oil Absorption	[illegible]8-32
Thru 200 mesh, %	98

Typical Particle Size Distribution:

Microns	% Less Than	Microns	% Less Than
40	90	5	5
30	76	4	[illegible]
20	50	2	1
10	16		

*Bacteria Controlled, CTFA, "Microbiological L[illegible]idelines for Cosmetic and Toiletries, 1[illegible] Combined count of less than 500 microorganisms per gram and the abs[illegible] gram negative bacteria.

G27

PLAINTIFF'S EXHIBIT
WCD-287

(2)