

CAUTION: Do not tint. This is a self-cleaning white house
If tinted, the cleaning action may cause streaking and

TIME-TEST REG. U. S. PAT. OFF.

*This product has been tested and approved by Time-Test
Laboratories for dependable service, uniformity of color
and consistently high quality.*

COPYRIGHT 1945, THE GLIDDEN CO.

IMPERIAL HOUSE PAINT

An exceptionally high grade finish for exterior surfaces. A specially prepared
repaint work when the surface to be recoated is in good condition for repainting.

DIRECTIONS

Stir thoroughly with a lifting motion. For a one
coat finish, apply as it comes from the can at a
rate of not more than 550 square feet per gallon;
do not add thinning oils or other paints to this
product. Should be used as White only—do not
tint.

SURFACES PREVIOUSLY PAINTED—All loose paint,
scales, blisters and dirt should be removed. Make
sure surface is dry. Spot-coat bare places with
Glidden Exterior Base Coat No. 1851. If the
surface is porous or weathered, apply a coat of
Glidden Exterior Base Coat No. 1851 over the

entire surface. Allow to
under good drying conditions
before Imperial House Paint

**TWO COAT SYSTEM FOR
FACES**—Prime Coat—Use
Coat No. 1851 at a spreading
rate of 550 square feet per gallon. Second
coat Imperial House Paint as a
finish, at a spreading rate of
550 square feet per gallon.

Select your brushes from
Line. L.C. 10-6-48.

ONE GALLON
U. S. MEASURE

Ingredients:
Titanium Dioxide 12.5%
Titanium Barium 29.5%
Titanium Magnesium 12.0%
Vehicle:
Linseed Oil 68.0%
Boys Bean Oil 8.5%
Long Oil 17.0%
Alkyd 5.5%
Mineral Spirits 5.5%
Liquid Driers 0.5%
Y-1867

CLEVELAND 2, OHIO • FACTORIES AND BRANCHES IN PRINCIPAL CITIES THROUGHOUT THE UNITED STATES

1867 OUTSIDE WHITE




Glidden

WARNING

May contain lead compound. Wash thoroughly after handling and before eating or smoking. Avoid breathing dust when wire brushing or sanding. Do not take internally. FLAMMABLE keep from heat and open flame.

Made in U. S. A.

ENDURANCE



HOUSE PAINT

• THE GLIDDEN COMPANY • *Everywhere on Everything*

N-1 SPC Inc. 1951

" Rymond 6
Vehicle 3

GLD 32402 A

This product has been tested and approved by Time-Tested Laboratories for dependable service, uniformity of color and consistently high quality.

IMPERIAL HOUSE PAINT

Stir thoroughly with a tilting motion. For a one coat finish, apply as it comes from the can at a rate of not more than 550 squares feet per gallon; do not add thinning oils or other points to this product. Should be used as White only—do not tint.

SURFACES PREVIOUSLY PAINTED.—All loose paint, scales, blisters and dirt should be removed. Make sure surface is dry. Spot-coat bare places with Glidden Exterior Base Coat No. 1851. If the surface is porous or weathered, apply a coat of Glidden Exterior Base Coat No. 1851 over the

entire surface. Allow to dry at least 48 hours under good drying conditions, then apply Endura-
ance Imperial House Paint, full body.

TWO COAT SYSTEM FOR NEW UNPAINTED SURFACES—Prime Coat—Use Glidden Exterior Base Coat No. 151 at a spreading rate of 450 square feet per gallon. Second coat—Use Glidden Imperial House Paint as a finish coat without thinning, at a spreading rate of 550 square feet per gallon.

Select your brushes from Glidden Related Brushline, L.C. 10-6-48.

GLD32103

[illegible]

Both NEED

wt 60.7%
oxide 34.3%
→ 35% lead
zinc oxide 46.0% "