Mr. Graber

Note attached.

Get Dope and see Dr. Jenkins
Also show Russell some of samples

E.A.D.
6/21

DSW 331046

Mr. Gerber

St L.

Lot 21 5460 McAuley

Color, NPA 2-

Softening Pt., ASTM 104.0

" " Std. 103.3

Acid No., NaOH/gm. .013

Cl 60.02

McCAULEY – ST. LOUIS

ANALYSIS OF AROCLOR 5460 LOT No. 21

COLOR, NPA	2–
SOFTENING POINT, ASTM	104.0
ACID No., NaOH/GM.	.013
CHLORINE	60.02%

GERBER

MONSANTO ANNISTON 5-6-41
MC CAULEY
ANALYSIS OF AROCLOR 5460 LOT NO 21
COLOR, NPA 2-
9SOFTENING POINT, ASTM 104.0
ACID NO., NAOH/GM. .013
CHLORINE 60.02 PER CENT
GERBER

DSW 331047