

RT-531-D
CG 40 CODE RT-531-D PKG.
→ AUG 24 80 36872
EST. WGT. 0 LBS.

Dry out.
(RT-160-P 27987-1-362#Nat 33.42%)

TOTAL WGT 121 #

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES RT-531-D (N) RT-531-D	APPROVED BY BBK 04-25-7 DCG 04-26-7
TYPED BY emw042977	
MAKING NOTES	

REMARKS

NAME: NAPHTHANIL® RED LIGHT

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS	12	26				HRS. WASHED					
NO. OF CAKES	36	40				OHMS					
PRESS without						HRS. WASHED					
WASH TO	4000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD on 3 cars						OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

Dry 24 hrs. at 160°F

LUMP: - OK - WET - SALTS - CONTAMINA

Dryer sections used:

ADDITIONAL DRYING HOURS REQUIRED

No. Drums:

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT.

RELEASED BY

-GRINDING-

MILL #4 LSP 1/8" RP SCREEN 2300 RPM

MAX. TEMP. 150°F

SCREEN

RPM

MAX. TEMP.

°F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 1 Pt Can

DELIVER TO C T L

DATE MIXED

SAMPLED BY

RELEASED BY