



COATINGS AND
PLASTICS
MATERIALS

BAKELITE® VINYL RESIN SOLUTION VYHH

FOR COATINGS

PRODUCT STANDARDS

DESCRIPTION

BAKELITE VYHH is a medium-molecular weight vinyl chloride-vinyl acetate copolymer resin. It dissolves readily in ketones, esters, chlorinated hydrocarbons, and combinations of these with aromatic hydrocarbons.

APPLICATIONS

BAKELITE VYHH is recommended for general coatings use.

FOOD ADDITIVE STATUS

BAKELITE VYHH is chemically identified in Food Additive Regulations §121.2514 for Resinous and Polymeric Coatings and by reference in §121.2526 for Components of Paper and Paperboard and in §121.2550 for Components of Closures.

Properties of

BAKELITE Vinyl Resin Solution VYHH

Properties	Test Methods	Required Values
Appearance	Visual	White powder
Size, per cent by weight, through a No. 20 USBS Sieve	WC-7-F	98, minimum
Heating Loss, 45 minutes at 105°C., per cent by weight	WC-160-H	3.0, maximum
Poly(vinyl chloride), per cent by weight	WC-294-B or D	85.0 - 86.5

(continued)

October, 1973
F-42808A

BAKELITE and UNION CARBIDE are registered trade marks of Union Carbide Corporation, U.S.A.

This information is not to be taken as a warranty or representation for which we assume legal responsibility nor as permission or recommendation to practice any patented invention without a license. It is offered solely for your consideration, investigation and verification.

UNION CARBIDE CORPORATION • 270 PARK AVENUE, NEW YORK, N.Y. 10017

UCC
063837

Solution Properties	Test Methods	Required Values
22 Per Cent Solution of Resin in 1:1 MIBK:Toluene		
Viscosity at 25°C., cps.	WC-31-W	200 - 400
Color, % transmission at 475 mμ/600 mμ	WC-5-K-2	85, minimum
Turbidity, light transmission at 600 mμ	WC-5-K-2	85, minimum
10 Per Cent Solution Resin 1:1 MIBK:Toluene		
Insoluble Matter, per cent by wet volume	WC-322-C	0.03, maximum

TESTING METHODS

Designated tests are made in accordance with current issues of ASTM or UNION CARBIDE (WC) Testing Methods. The former can be obtained from the American Society for Testing and Materials, Philadelphia, Pa., while the latter are available from Union Carbide Corporation upon request.

LABELING

All containers of BAKELITE Vinyl Resin Solution VYHH are plainly marked with the product nomenclature, blend number, and net weight. Shipments will be so addressed as to provide complete delivery to the purchaser.

PRECAUTIONARY LABELING

On the basis of the toxicological, physical, and chemical properties of BAKELITE Vinyl Solution Resin VYHH, precautionary labeling used on the containers is as follows:

FOR INDUSTRY USE ONLY