

Hylo Finishing Cement	4.8 to 5.5 (1963-1967) 2.7 to 6.9 (1968-9/1971)
Hi-Stick Insulating Cement	4.3 to 6.3 (1964-1969)
"33" Insulating Cement	7.8 to 10.8 (1935-1944) 13.8 to 14.7 (1945-1949)
"99" Finishing Cement	72.2 to 82.6 (1935-1962)
"106" Finishing Cement	25.2 to 28.5 (1948-1962)
"111" Finishing Cement	2.1 to 3.7 (1935-1966)
"330" Insulating Cement	8.9 to 10.0 (1939-1940) (1942&1945)
"1003" Finishing Cement	4.7 (1947 only)
Navy Grade Cement	14.6 to 16.2 (1955-1956) 8.3 to 8.8 (1958-1959)
Navy Special Cement	11.9 (1945 only)
MASTICS:	
Insulseal	16.8 to 20.8 (1935-1968)
Insulseal-All Purpose	6.0 to 6.9 (1968-1969)
Insulstic-Towel Grade	12.5 to 16.0 (1939-1962)
Insulstic-Brush Grade	7.1 to 16.4 (1942-1953) 7.5 to 13.5 (1957-1959)
Swetchek	1.6 to 11.3 (1945-1947) 1.5 to 1.9 (1948-1961)
BLOCK:	
Vercel Block	4.1 to 7.5 (1937-1944)
DE 85 Block	4.2 to 10.3 (1947-1953)
DE 95 Block	9.7 (1949) 4.0 to 9.1 (1950-1953)