

HARDNESS 70+/-5

STOCK NO. 03260

-1

CKR PVN 072

COMPOUNDED BY

06/05/89

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	100.00	71.94	45.89	200.00
006	DINP	59.00	59.60	27.07	118.00
017	PARALEX G-62	3.00	3.03	1.37	6.00
030	CAMEL WITE	40.00	14.81	18.35	80.00
053	STEARIC ACID DP	.40	.50	.18	.80
146	SYNPRON 1530	2.50	2.40	1.14	5.00
90200	CHLORWAX LV	13.00	11.82	5.96	26.00

TOTAL	217.90	164.10	99.99	435.80
-------	--------	--------	-------	--------

.56	-	PHYSICAL PROPERTIES		
	-		SPEC.	MIN. MAX.
USE	-	SPECIFIC GR.	1.328	
	-	HARDNESS		
REPLACES	-	TENSILE		
	-	ELONGATION		
REASON	-	MODULUS @		
	-	MOONEY @		
COLOR	-	SCORCH		
	-	CURE		
REQUIRMENTS TO MEET	-	STOCK CONTROL TEST		
	-			
LAB	-			
COST	-			
MIXING	-			
	-			

CHARDO 00088

HARDNESS 70+/-5

STOCK NO. 03260 -1

CKR PVN 072

COMPOUNDED BY

06/05/89

APPROVED BY

CODE	MATERIALS	100 RHC	VOL.	100%	200 RESIN BATCH
001	VINYL RESIN	100.00	71.94	45.89	200.00
006	DINP	59.00	59.60	27.07	118.00
017	PARALEX G-62	3.00	3.03	1.37	6.00
030	CAMEL WITE	40.00	14.81	18.35	80.00
053	STEARIC ACID DP	.40	.50	.18	.80
146	SYNPRON 1530	2.50	2.40	1.14	5.00
90200	CHLORWAX LV	13.00	11.82	5.96	26.00

TOTAL	217.90	164.10	99.99	435.80
-------	--------	--------	-------	--------

.56	-	PHYSICAL PROPERTIES		
USE	-	SPEC.	MIN.	MAX.
REPLACES	-	SPECIFIC GR.	1.328	
REASON	-	HARDNESS		
COLOR	-	TENSILE		
REQUIRMENTS TO MEET	-	ELONGATION		
	-	MODULUS @		
	-	MOONEY @		
	-	SCORCH		
	-	CURE		

STOCK CONTROL TEST

LAB	-
COST	-
MIXING	-

CHARD0 00089

