

200

EST. WGT. 1128 LBS.

EST. WGT. 1128 LBS.

PROCESSES	APPROVED BY
KY-781-D (N)	FWP 10-13-77
	AMJ 10-13-77

TYPED BY
emw101378

MAKING NOTES

REMARKS

Total Wgt. 4428#

NAME: KROLOR® YELLOW LIGHT

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT			240			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE			4-25			ST/RTED	8:20 AM				
TIME			9 AM			CAKES USED	216				
RELEASED BY			SK			WATER ON	10				
PRESS	2	22	23	24		HRS. // SHED	10				
NO. OF CAKES	46	46	46	52		OHMS	5750				
PRESS	with	AGITATION				HRS. W/ SHED					
WASH TO	5000	OHMS with 35-75°F water				OHMS					
TEST AFTER	4	HOURS				HRS. WASHED					
LOAD	on 6 cars					OHMS					

AMPLIES 1-8 oz jar
DELIVER TO CTL FOR COLOR

SAMPLED BY _____ RELEASED BY _____

- DRYING -

RY	16	HOURS AT	220	°F	LUMP - OK - WET - SALTS - CONTAMINATE
					Color Loss due to salts
					Containing in box

ADDITIONAL DRYING HOURS REQUIRED

AMPLIES	NO. CARS PULLED	LUMP WGT. 3963
DELIVER TO	SAMPLED BY	RELEASED BY PH

-GRINDING-

WILL 939	HSP	3/32"	RP	SCREEN	3500	RPM	SCREEN		RPM
MAX. TEMP.			210°F				MAX. TEMP.		°F

EXPLAIN LOSSES

AMPLE WITHOUT MIXING
AMPLES 1 Env & 1 Pt Can
DELIVER TO CYL

DATE MIXED	
SAMPLED BY	RELEASED BY

DUP050096234

11/8
12
365

3.16 +
0.12 -
3.16 +
0.12 -
3.12 +
0.12 -
3.18 +
0.12 -
3.14 +
0.12 -
3.22 +
0.12 -
3.27 +
0.12 -
3.31 +
0.12 -
3.23 +
0.12 -
3.44 +
0.12 -
3.35 +
0.12 -
3.24 +
0.12 -
2.37 +
0.12 -
39.63 *
39.63M+