Dutch Boy

SATIN FINISH ENAMEL

II-09 DEEP BLENDING BASE

112 U.S. STD. FL. OZ.

TRADE MARKS REG. U.S. PAT. OFF.

N13865

0000-NLI-0000020602

Dutch Boy SATIN FINISH ENAMEL

Semi-Gloss Finish for Walls and Woodwork

A modern alkyd resin enamel for use on walls, woodwork, cabinets and fixtures, whenever a smooth, hard, semi-gloss enamel finish is desired. Resistant to soiling and readily cleaned. Available in all of the modern, appealing colors of the Dutch Boy Color Gallery.

Follow Directions—STIR WELL—*No Thinner Needed*

Be certain the surface is clean and dry; free from oil, grease, wax or dirt.

Prepare the surface by removing all loose or scaling paint, repairing damaged areas and patching large cracks in plaster. Glossy surfaces should be sanded lightly.

Surfaces such as large areas of plaster, wallboard, etc., which have not been previously painted, or those which are porous, not uniform or in poor condition, should be painted first with Dutch Boy Wall Primer & Sealer. Or Dutch Boy Enamel Undercoat should be used first for a smooth finish on woodwork, cabinets, etc.

Stir well, making certain the paint is completely uniform. Apply with brush or roller coater at a rate of about one gallon for every 500 square feet of surface.

One coat of Dutch Boy Satin Finish Enamel is usually sufficient on surfaces previously painted with eggshell, semi-gloss or gloss finishes which are uniform and in good condition. If a second coat should be required, wait overnight until the first coat is dry and hard and sand it lightly.

When more than one container of the same color is to be used, mix these together, either before starting or while the work is in progress.

WARNING: Inflammable. Keep away from heat and open flame. Use with adequate ventilation. Avoid prolonged breathing of vapors and prolonged contact with skin. Wash thoroughly after using and before eating or smoking. Do not take internally.

COMPOSITION OF PAINT BY WEIGHT

PIGMENT 44.8%

Titanium Calcium Pigment	41.9%
Zinc Oxide	4.2%
Calcium Carbonate	38.9%
Magnesium Silicate	15.0%

VEHICLE 55.2%

Soya Alkyd Resin	43.2%
Mineral Spirits	51.8%
Liquid Drier	5.0%



EL

NATIONAL LEAD COMPANY

GENERAL OFFICES: 111 BROADWAY, NEW YORK 6, N. Y.

SALES OFFICES: ALL PRINCIPAL CITIES