

PRODUCT NAME = MOLYBDATE ORANGE

CG 01 CODE YE-698-D PKG

LOT F2J54

JUN 4 1982

EST. WT. 5547* LBS.

NON-BLEEDING

PROCESSES APPROVED BY
YE-698-D (S) F. POST 10709781
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS		PRESSING =	RECORD				
VAT			1ST	2ND	3RD	4TH	5TH
DATE	245	PRESSLOAD	8AM				
TIME	3:17	STARTED	54				
RELEASED BY		CAKES USED	53				
PRESS	2 92 93	WATER ON	3 1/2				
NO. OF CAKES	54 54 54	M MHOS	22				
PRESS WITH AGITATION		HRS. WASHED					
WASH TO 500 M MHOS WITH 35-75* WATER		M MHOS					
TEST AFTER 2 HOURS		HRS. WASHED					
LOAD ON 7 CARS		M MHOS					
		CAKE CONDITION	6				
		NO CARS LOADED					
		EXPLAIN LOSSES					

SAMPLES 8 OZ
DELIVER TO CTL.

SAMPLED BY
RELEASED BY

DRYING =
(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLE
DELIVER

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

CO-GRIND PER CTL INSTRUCTIONS GRINDING
MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

EXPLAIN LOSSES

SAMPLE
SAMPLES 1 ENV IF GROUND SEPARATELY
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

N39427

54
41
231
0
285
12
290
12
285
12
309
12
305
12
304
12
320
12
285
12
315
12
285
12
300
12
310
12
290
12
310
12
310
12
315
12
305
12
310
12
305
12
140
12
5638