

AMERICAN NATIONAL
STANDARD

ANSI/ASTM D 1869 - 78

AMERICAN SOCIETY FOR TESTING AND MATERIALS

1916 Race St., Philadelphia, Pa. 19103

Reprinted from the Annual Book of ASTM Standards, Copyright ASTM
If not listed in the current combined index, will appear in the next edition.

Standard Specification for RUBBER RINGS FOR ASBESTOS-CEMENT PIPE¹

This Standard is issued under the fixed designation D 1869; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval.

1. Scope

1.1 This specification covers rubber rings used to seal the joints of asbestos-cement pipe conforming to Specifications C 296, C 428, C 644, and C 668.

1.2 A specification is given for (1) natural or synthetic rubber rings, or both, where resistance to oil or solvents is not required, and (2) synthetic rubber rings for services involving resistance to oil or solvents.

2. Applicable Documents

2.1 ASTM Standards:

- C 296 Specification for Asbestos-Cement Pressure Pipe²
- C 428 Specification for Asbestos-Cement Nonpressure Sewer Pipe²
- C 644 Specification for Asbestos-Cement Nonpressure Small-Diameter Sewer Pipe²
- C 668 Specification for Asbestos-Cement Transmission Pipe²
- D 395 Tests for Rubber Property—Compression Set³
- D 412 Tests for Rubber Properties in Tension⁴
- D 573 Test for Rubber Deterioration in an Air Oven³
- D 865 Test for Rubber Deterioration by Heating in a Test Tube³
- D 1415 Test for Rubber Property—International Hardness³
- D 2137 Test for Rubber Property—Brittleness Point of Flexible Polymers and Coated Fabrics³
- D 2240 Test for Rubber Property—Durometer Hardness⁶

3. Composition and Manufacture

3.1 The ring shall consist of a properly

vulcanized virgin rubber compound. Virgin rubber is defined as one containing no scrap, reclaim, or rubber substitutes.

3.2 If a joint is used in the manufacture of the ring, the strength of the spliced joint shall be such that the ring will withstand the stretch test described in 8.8 with no visible separation or peeling.

4. Physical Requirements

4.1 Sample rings taken from the shipment shall conform to the requirements for physical properties prescribed in Table 1 when tested in accordance with the methods specified in Section 8.

5. Dimensions and Tolerances

5.1 The rings shall conform to the dimensions specified by the manufacturer of the pipe in which the rings are to be used, with a RMA Class 3 tolerance of ± 0.25 up to 25 mm (± 0.010 up to 1 in.) on all cross-section dimensions, and $\pm 1\%$ on all diametral dimensions, unless otherwise agreed upon by the pipe manufacturer and the ring supplier.

NOTE—The design and tolerances of asbestos-cement pipe are not sufficiently standardized to permit interchangeability of rings in many cases from pipe of one manufacturer to that of another.

¹ This specification is under the jurisdiction of ASTM Committee D-11 on Rubber and Rubber-Like Materials and is the direct responsibility of Subcommittee D11.36 on Seals.

Current edition approved April 28, 1978. Published July 1978. Originally published as D 1869 - 61 T. Last previous edition D 1869 - 66 (1972).

² Annual Book of ASTM Standards, Part 16

³ Annual Book of ASTM Standards, Part 37

⁴ Annual Book of ASTM Standards, Parts 35, 37, and 38.

⁵ Annual Book of ASTM Standards, Parts 37 and 38.

⁶ Annual Book of ASTM Standards, Parts 35 and 37



6. Workmanship

6.1 The surface shall be smooth and free of pitting, cracks, blisters, air marks, and any other imperfection that would affect its behavior in service. The body shall be free of porosity and air pockets.

6.2 The flash thickness shall not exceed 0.4 mm (0.015 in.), nor the flash width 0.8 mm (0.03 in.) at any point in the ring.

6.3 Offset, or failure of the mold to register accurately, shall not exceed 0.4 mm (0.015 in.).

7. Sampling

7.1 A number of sample rings shall be drawn at random from each shipment of rings in accordance with Table 2.

7.2 These shall be stretched and examined as specified in 8.8. A sufficient additional number of rings shall be drawn at random for the tests specified in Table 1.

8. Test Methods

8.1 *Tensile Strength, Elongation, and Stress at 300 % Elongation*—Methods D 412:

8.1.1 Cut samples for tensile strength, elongation, and stress at 300 % elongation tests from circumferential sections of the ring itself.

8.1.2 From these samples stamp dumbbell test specimens using a standard ASTM Type C dumbbell conforming to Fig. 1 of Method D 412.

8.1.3 The sections from which the dumbbells are cut may be prepared by sectioning a sample ring held rigidly in a jig, which in turn is mounted in a chuck of a machinist's lathe. A sharp, thin cutting knife should be mounted in the lathe holder and the cut made at a right angle to the jig face. The cutting site should be lubricated at all times by a jet of cool water.

8.1.4 These sections may be buffed lightly prior to cutting into dumbbell specimens in order to bring them to a uniform thickness for testing.

8.2 *Hardness*:

8.2.1 Method D 1415 shall be used as the reference method.

8.2.2 Method D 2240 may be used for quality control.

8.2.3 Hardness readings for guidance pur-

poses may be taken directly on the ring, recognizing that those may vary slightly from those taken on dumbbell specimens.

8.3 *Air Aging: Tensile Strength, Elongation, and Hardness*:

8.3.1 Methods D 865 (preferred) or D 573, in conjunction with Methods D 412 and D 1415 or D 2240. Prepare test specimens in accordance with 8.1.

8.3.2 Age nonoil-resistant specimens for 166 ± 2 h at $70 \pm 2^\circ\text{C}$.

8.3.3 Age oil-resistant specimens for 70 ± 0.7 h at $100 \pm 2^\circ\text{C}$.

8.4 *Water Aging: Volume and Appearance Change*:

8.4.1 Cut one specimen 50 ± 3 mm (2.0 $\pm$ 0.1 in.) long and not less than 13 mm² (0.2 in.²) in cross section from each of three rings.

8.4.2 Totally immerse the specimens in the siphon cup of an insulated 3-dm³ extraction apparatus, and hold at a temperature of $100 \pm 2^\circ\text{C}$ for 20 consecutive days. Suspend the specimens at least 50 mm (2 in.) beneath the surface of the water in such a manner that they do not contact one another or the surface of the cup.

8.4.3. Immediately after removal from the boiling water, blot the specimens, weigh and calculate the volume increase in accordance with Method D 471.

8.4.4 Average the values obtained for the three specimens.

8.5 *Compression Set*:

8.5.1 Method B of Methods D 395, except cut three specimens from separate rings about 75 mm (3 in.) in length and the full cross-sectional area of the ring in a compression device 50 mm long.

8.5.1.1 Place the specimens in the compression device with the inside and outside circumference sides in contact with the compression plates.

8.5.1.2 If this is impractical because of the size or shape of the specimens, they may be placed in the compression device in a manner that will give the most accurate values.

8.5.2 Make a reference measurement at any convenient point where the section is solid and compress the specimen 50 % at the reference point, using spacers.

8.5.3 Oven age nonoil-resistant specimens for 22 ± 0.25 h at $70 \pm 2^\circ\text{C}$.

8.5.4 Oven age oil-resistant specimens for

22 ± 0.25 h at 100 ± 1°C.

8.6 *Low-Temperature Flexibility:*

8.6.1 Method D 2137.

8.6.2 Prepare test specimens in accordance with 8.1.2 through 8.1.5. The temperature of test shall be -25 ± 2°C.

8.7 *Oil Aging: Tensile Strength, Elongation, Hardness, and Volume Change:*

8.7.1 ASTM Method D 471.

8.7.2 Prepare test specimens for tensile strength, elongation, and hardness tests in accordance with 8.1.2 through 8.1.5.

8.7.3 Prepare specimens for the volume change test in accordance with 8.4.1.

8.7.4 Immerse the specimens in ASTM Oil No. 3 for 70 ± 0.7 h at 100 ± 2°C.

8.8 *Stretch Test for Visual Examination:*

8.8.1 Stretch the rings until the circumference has increased 50 %.

8.8.2 Inspect each ring visually for defects in accordance with 3.2 and 6.1.

8.8.3 The number of rings to be examined and the maximum number of defective rings for acceptance of the lot is shown in Table 2.

9. **Markings and Color Coding**

9.1 Each ring shall be marked with clearly legible letters, the size of which shall not exceed 6 mm (1/4 in.).

9.2 The markings shall include the ring manufacturer's name or symbol, the pipe manufacturer's name or symbol, the pipe size and pressure rating, and the year of manufacture.

9.3 Each oil-resistant synthetic rubber ring shall be marked with a color stripe, dot, or other identifying mark to distinguish this ring from the nonoil-resistant type.

9.3.1 The shape and color of the mark shall be as specified by the manufacturer of the pipe in which the ring is to be used.

TABLE 1 Physical Requirements of Rubber Rings for Asbestos-Cement Pipe

Test	Type of Rubber Ring	
	Nonoil-Resistant	Oil-Resistant
Original Properties:		
Tensile strength, min, MPa (psi):		
Average of three specimens	14.0 (2000)	10.5 (1500)
Lowest individual	12.5 (1800)	9.0 (1300)
Elongation, min, %:		
Average of three specimens	350	325
Lowest individual	325	300
Hardness number ^a	nominal ± 5	nominal ± 5
Stress at 300 % elongation, MPa (psi):		
Max	16.0 (2300)	16.0 (2300)
Min	8.4 (1200)	7.0 (1000)
Compression set, max, %	16	25
Low-temperature flexibility	no cracks	no cracks
After Oven Aging:		
Tensile strength, average decrease, max, %	15	20
Elongation, average decrease, max, %	25	30
Hardness, average increase, max, points	7	15
After Water Aging:		
Volume change, max, %	12	12
Appearance change	no surface degradation	no surface degradation
After Oil Aging:		
Tensile strength, average decrease, max, %		35
Elongation, average decrease, max, %		40
Hardness, average change, points		-10 to +2
Volume change, average, %		-1 to +15

^a Nominal hardness shall be from 50 to 60 as specified by the pipe manufacturer

TABLE 2 Sampling Plan for Stretch Test for Visual Inspection

Number of Rings in Ship- ment	Number of Rings in Sample	Maximum Number of Defectives for Accept- ance
Up to 800	75	4
801 to 3 200	150	8
3 201 to 8 000	225	11
8 001 to 22 000	300	14

The American Society for Testing and Materials takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, is entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, 1916 Race St., Philadelphia, Pa. 19103, which will schedule a further hearing regarding your comments. Failing satisfaction there, you may appeal to the ASTM Board of Directors.