

DELCO MORaine CHEMICAL ANALYSIS
OF RETURNED CADILLAC LINING (EO P1389-685)

<u>Lining</u>	<u>Gogal Hardness</u>	<u>Sp. Gr.</u>	<u>Acetone Extraction</u>	<u>Ignition Loss</u>
<u>Pri.</u> Spec.	GCS 15-41	1.81 - 1.99	4.0% Max.	31-35%
From test 0301-1	25, 25	1.81	3.3	---
New pc. from same lot as 0301-1	21, 21	1.83	3.4	36
From old lot	18, 21	1.86	2.3	35.4
 <u>Sec.</u> Spec.	 GC 17-36	 1.89 - 2.07	 2.5% Max.	 34-38%
From test 0301-1	21, 24	1.96	2.7	35.6
New pc. from same lot as 0301-1	22, 25	1.94	2.6	36.4
From old test	20, 20	1.99	2.6	36.1

B. L. Hirsch
6-13-79

/blw

SC1 02437