

NAME: MOORWHITE EXTERIOR PAINT COLOR: WHITE
 CATEGORY: I QUALITY: FIRST

PIGMENT: 70.0% LBS. GAL. YIELD UNIT COST TOTAL COST

White Lead Carbonate	500	8.95	.08-1/4 lb.	41.25
Titanox RC	250	9.23	.05-1/2 lb.	13.75
Asbestine	250	10.53	1.05 cwt.	2.63
Barytes	350	9.45	1.32 cwt.	4.62
Titanox A-24	150	4.74	.15 lb.	22.50
VEHICLE 30.0%				
Raw Oil	420	54.0	.132 lb.	55.44
#3878-R	142	18.0	.75 gal.	13.50
Varsol	52	8.0	.082 gal.	.66
#10-R	29	4.0	.44 gal.	1.76

CALCULATED YIELD 2143 126.90 156.11

MANUFACTURED LOSS 2.3%

ACTUAL YIELD 124 Gals.

COST ANALYSIS

MATERIAL COST PER GAL. OR LB. (TOTAL COST DIVIDED BY ACTUAL YIELD) . . . 1.259
 DIRECT LABOR COST PER GAL., OR LB.053
 FACTORY OVERHEAD PER GAL., OR LB.069
 BULK COST PER GAL., OR LB.1.381
 COMPLETE PACKAGE COST PER GAL., OR LB. (CONTAINER PLUS FILLING EXPENSE)139
 FACTORY COST IN PACKAGE PER GAL., OR LB.1.52

PRICES

SHOW THE HIGHEST NET UNIT PRICE WHICH WAS CHARGED OR WHICH WOULD HAVE BEEN CHARGED IN MARCH 1942, TO EACH OF THE FOLLOWING TYPES OF BUYERS OR TRANSFEREES:

- (A) TO A COMPANY OWNED OR CONTROLLED OUTLET
- (B) TO AN INDEPENDENT WHOLESALER
- (C) BY COMPANY CONTROLLED OUTLET TO RETAIL CUSTOMER
- (D) TO AN INDEPENDENT RETAILER (DEALER)
- (E) TO OTHER (SPECIFY)

1.896

2.37