REPRODUCED AT THE NATIONAL ARCHIVES

FORMULAS OF SPECIFIED PAINTS AND VARNISHES
Produced by Three Manufacturers in Chicago, January 1941 - June 1942

MANUFACTURER 'A'

Orange Shellac (621)

Percentage Formula			Working or Vat Formula		
January 1941 to January 1942			January 1941 to January 1942		
	Percent			Gals.	Lbs.
[illegible]		35	Denatured Alcohol	100	678
			Ansol	12½	83
[illegible] Shellac	98.5		Orange Shellac		412½
[illegible] Acid	1.5		Oxalic Acid		9
	100.0				
[illegible]		65			
[illegible] Alcohol	90				
[illegible]	10				
	100				
		100			

Black Heat Resisting Paint (6405)

Percentage Formula			Working or Vat Formula		
January 1941 to January 1942			January 1941 to January 1942		
	Percent			Gals.	Lbs.
[illegible]		35	Carbon Black		21
			Asbestine		166
[illegible] Black	6		Silica		166
[illegible]	47		Black Asphaltum	21.58	
[illegible]	47		Roof Coating Vehicle	7	
	100				
		65	Grind		
			Black Asphaltum	39.75	
[illegible] Base	73		Oleum	17.3	
[illegible] Marine Oil	9		Cobalt Drier	.4	
[illegible] Spirits	17		Japan Drier	.4	
[illegible] Drier	1				
	100	100			