

AROCLOR® PLASTICIZERS

A series of inert, chemically-resistant, fire-retarding
plasticizers compatible with wide variety of resins.

PLASTICIZERS



"Nothing contained herein is to be construed as a recommendation to use any product in conflict with
any patent. MONSANTO MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY
OF ANY PRODUCT'S REFERRED TO, no guarantee of satisfactory results from reliance upon con-
tained information or recommendations, and disclaims all liability for any resulting loss or damage."

Organic Chemicals Division / 800 N. Lindbergh Blvd. / St. Louis, Missouri 63166

0145038

LEXOLDMON003631

AROCLOR® PLASTICIZERS

A series of inert, chemically resistant, fire retarding plasticizers compatible with a wide variety of resins.

0145039

LEXOLDMON003632

Table of Contents

	<u>Page</u>
Properties as Plasticizers	2
Key to Nomenclature	3
Applications by Product	6
Aroclor® Markets	8
Formulations:	
Delayed Tack Adhesives	10
Emulsion Adhesives	11
Pressure Sensitive Adhesives	13
Hot Melt Adhesives	15
Polysulfide Sealants	17
Chlorinated Rubber Coatings	18
Acrylic Lacquer	19
Physical Properties	20
Toxicity and Safe Handling	22

Properties as Plasticizers

The Aroclor® resins/plasticizers and their blends have an unusual combination of properties which make them extremely useful products. Their most important characteristics are:

- Low Cost
- Highly Compatible
- Chemically Stable
- Fire Retardant
- Excellent Adhesion

Another very useful aspect of this product line is the fact that a continuous range of properties can be achieved by using combinations of the Aroclors and their blends. Some of the physical properties which can be controlled through product selection are shown on the following pages.

Our Aroclor® product line is now made up of polychlorinated terphenyls, monochlorinated biphenyl, and blends of these products. None of these materials has been shown to create any environmental problems. On the other hand, Food and Drug Administration approval has not been obtained for any of these products. Accordingly, the Aroclor® plasticizers should not be used in connection with food or food-related products, with food wrapping or food container materials. Further, Monsanto strongly recommends that these products not be used in any other application such as non-FDA regulated food systems, in potable water systems, in any animal feeding systems, or in pharmaceuticals.

Key to Nomenclature

5400 Series

These products are chlorinated terphenyls. The last two digits indicate the chlorine content of the material, e.g., Aroclor® 5460 is a chlorinated terphenyl with 60 percent chlorine. Undistilled Aroclors® are available and are designated by a 5000 series vs. the 5400 series. They are somewhat higher in color but otherwise have product characteristics similar to the distilled products.

6000 Series

These products are blends of Aroclor® 5460 and Aroclor® 1221-B, a biodegradable monochlorinated biphenyl. The last two digits are an indication of the proportion of Aroclor® 5460 in the blend, e.g., Aroclor® 6062 has more Aroclor® 5460 in it than does Aroclor® 6050.

Miscellaneous Blends

Other product blends containing such other materials as Santicizer 140 for improved fire retardancy, or toluene/xylene for lower viscosities will also be made available as the demand for these specialty products develops.

AROCLORS

	<u>5432</u>	<u>5442</u>	<u>5460</u>
Adhesion/Tack	_____	increasing	_____➔
Hardness	_____	increasing	_____➔
Flexibility	_____	decreasing	_____➔
Fire Retardance	_____	increasing	_____➔
Volatility	_____	decreasing	_____➔
Chlorine Content	_____	increasing	_____➔
Viscosity	_____	increasing	_____➔
Density	_____	increasing	_____➔
Permanence	_____	increasing	_____➔
Compatibility	_____	decreasing	_____➔

AROCLOR BLENDS

	6040	6050	6062	6070	6090
Adhesion/Tack	—	—	increasing	—	—
Hardness	—	—	increasing	—	—
Flexibility	—	—	decreasing	—	—
Fire Retardance	—	—	increasing	—	—
Volatility	—	—	decreasing	—	—
Chlorine Content	—	—	increasing	—	—
Viscosity	—	—	increasing	—	—
Density	—	—	increasing	—	—
Permanence	—	—	increasing	—	—
Compatibility	—	—	decreasing	—	—

Applications by Product

Listed below are some of the applications where these products can be used:

Aroclor Blends

- | | |
|------|---|
| 6040 | Polyvinyl Acetate Emulsion Adhesives
SBR Adhesives

Miscellaneous applications where a high degree of flexibility is required. |
| 6050 | Chlorinated Rubber and other Resin systems for Coatings.

Inks |
| 6062 | Polysulfide Sealants/Adhesives
Chlorinated Rubber Coatings and Adhesives
SBR Coatings and Adhesives

Miscellaneous applications where high chlorine content, high tack, are required.

Inks |
| 6070 | Polysulfide Adhesives
Chlorinated Rubber Adhesives

Miscellaneous applications where very high chlorine content and very high tack are required. |
| 6090 | Radiation Curing Applications |

Aroclors

5432	Polysulfide Sealants/Adhesives Chlorinated Rubber Coatings and Adhesives SBR Coatings and Adhesives
5442	Surface Coatings
5460	Hot Melt Adhesives, Surface Coatings

0145046

LEXOLDMON003639

AROCLOR MARKETS

<u>Aroclor Applications</u>	<u>Polymers and/or Binders</u>	<u>Aroclor Recommended</u>
<u>Adhesives</u>		
Delayed Tack	SBR, PVAc, PS	6090, 5460
Emulsion	PVAc, SBR, Acrylic-VAc, Acrylic-ethylene	1221-B, 6040, 6050
Pressure Sensitive	Natural Rubber, SBR, Cl Rubber	1221-B, 6062, 5460
Hot Melt	EVAc, PVB, Phenoxies, Polyamides	5460, 5465, 5060, Montar 5
<u>Sealants</u>		
	Polysulfide, Nitrile Epoxy, Polyurethane	5460/S-261, HB-40, 6070, 5432
<u>Caulking Compounds</u>		
	Acrylics	5460, 6070
<u>Surface Coatings</u>		
Paints	PVAc, PVC, Nitriles, Styrene, Acrylics	5460, 6062, 6070
Lacquers	Alkyd, Cl Rubber	5460, 6062, 6070, 6090

AROCLOR MARKETS (Continued)

<u>Aroclor Applications</u>	<u>Polymers and/or Binders</u>	<u>Aroclor Recommended</u>
<u>Surface Coatings (Continued)</u>		
Varnish	Polysulfide	6070
Paper Coatings	Ethyl Cellulose	6040, 6050
<u>Printing Inks</u>	Nitrocellulose, Acrylic	5460, 6070, 6062, 6090
<u>Miscellaneous</u>		
Lost Wax Casting	Wax	5442, 5460, 5465
Impregnating Phenolic Resistors	Resinox, PVC	5460, 6062
Laminating Resins	Phenolic	5460, 6070
Epoxy Resins	Epoxy	6062, 6070

0145048

DELAYED TACK ADHESIVES

Total Market for Plasticizers: 3-4 Million Pounds/Year

Typical Formulations:

<u>Component</u>	<u>Parts by Weight</u>
1. Diphenyl Phthalate	60.6
Cumar W 12	15.1
Lustrax 15	24.3
2. Vinsol Resin	50.0
Santicizer 1-H	50.0
Acrysol M. R.	10.0
Thinned amine dispersant	250.0
<u>Thinned amine dispersant</u>	
Steric Acid	1
Poly-pale Resin	1
2-amino-2-methyl-1-propanol	1
Water	3

Properties Desired:

1. Activation at specific temperature.
2. Remains tacky for specific time period.
3. Remains bonded over wide temperature range.

Current Recommendations:

1. Dicyclohexyl Phthalate - DCHP
2. Diphenyl Phthalate
3. Santicizer 1-H
4. Aroclor 5460
5. Aroclor 6090

0145049

EMULSION ADHESIVES

Total Market for Plasticizers: 35-40 Million Pounds/Year

Typical Formulations:

Gelva S-55	90	Gelva TS-65	90
Santicizer 218-A	10	Santicizer 885	10
	<u>100</u>		<u>100</u>
Gelva S-77	90	Gelva TS-100	90
Aroclor 1221-B	10	Aroclor 6040	10
	<u>100</u>		<u>100</u>
Aircoflex 400	95	Gelva TS-100	65
Aroclor 6050	5	Aroclor 1221	10
	<u>100</u>	Staybelite Ester 10	15
		Butyl Acetate	10
		Santomerse SX	0.1
			<u>100.1</u>

Properties Desired:

1. Controlled wet tack: in most cases, the shorter the wet tack time before the adhesive grabs, the better.
2. Open time of at least one minute: open time is the time during which two adhered substrates can be adjusted after making contact.
3. Physical properties of adhesive film: the cohesive strength of the adhesive must be strong enough to hold the substrates together.

EMULSION ADHESIVES (Continued)

4. Relatively high heat delamination temperature: this depends on the film forming polymers, the type and amount of plasticizer.
5. Good resistance to water: prolonged immersion in water causes loss of adhesion by most emulsion adhesives at elevated temperatures.

PRESSURE SENSITIVE ADHESIVES

Total Market for Plasticizers: 30 Million Pounds/Year

Typical Formulations:

<u>Component.</u>	<u>Parts by Weight</u>
1. <u>Calendered into Fabric</u>	
Cellulose Acetate	1
Sarticizer 8	3
Sartolite MHP	2
2. <u>Hot Melt Type</u>	
Crepe Rubber	15
Polyisobutylene	15
Ester Gum	20
Santolite MHP	20
Aroclor 6070	30
Wax	10

Properties Desired:

1. Low volatility
2. Good heat stability
3. High flow/spreadability at elevated temperatures
4. Good moisture resistance
5. Broad use temperature range

PRESSURE SENSITIVE ADHESIVES (Continued)

Current Recommendations:

1. Santicizer 160
2. Santicizer 148
3. Aroclor 5460, 6040, 6070
4. Santclite MHP

0145053

HOT MELT ADHESIVES

Total Market for Plastifier/Tackifier: 30-40 Million Pounds/Year

Typical Formulations:

<u>Component</u>	<u>Parts by Weight</u>
1. <u>Basic Formula</u>	
EVA:	30
Aroclor 5460	40
Microcrystalline Wax	30
2. <u>Alkali Dispersable Bookbinding Adhesive</u>	
PVA:	40
Santicizer 160	8
Aroclor 5432	26
Nevellac Hard	24
Acrowax C	1
Sodium Benzoate	0.75

Properties Desired:

1. Good heat stability
2. Sharp melting point
3. Satisfactory viscosity/temperature relationship
4. Bond flexibility
5. Adhesion

HOT MELT ADHESIVES (Continued)

Current Recommendations:

1. Aroclor 5460, 5465
2. Aroclor 5060, Montar 5
3. Santicizer 160, 141, 148
4. Santicizer 8

POLYSULFIDE SEALANTS

Typical Formulation:

Thiokol GP-2	100
Lead dioxide paste (50% PbO ₂ , 45% S-160, 5% St. acid)	15
Plasticizer	<u>30</u> <u>145</u>

Fillers such as SRF black, MT black, Lithopone, Zinc Sulfide and York Whiting may be included in the 15 to 75 phr range.

Properties Desired:

1. Adhesions
2. Specific Rate of Cure
3. Specific Creep Characteristics
4. Shelf Stability
5. Pot Life

Current Recommendations

1. Santicizer 261
2. HB-40
3. Blends of Aroclor 5460/S-261 (Santicizer 326)
4. Aroclor 5460/S-160
5. Santicizer 148

CHLORINATED RUBBER COATINGS

Typical Formulation:

Parlon S-10	35
Epon 828	1
Epichlorohydrin	0.2
Xylene	100
Plasticizer	25
TiO ₂	38.4
Carbon Black	<u>C.4</u> <u>200.0</u>

Properties Desired:

1. Water impermeability
2. Chemical resistance
3. Adhesion to substrate
4. Flexibility

Current Recommendations:

1. Aroclor 6062
2. Aroclor 5432
3. Phthalate ester (if not chem. resistance req.)
4. Aroclor 5460/Santicizer 711 3/1 or 4/1

ACRYLIC LACQUER

Typical Formulation:

Lucite 6011 or 6012	250 (~100 solids)
1/2 sec. cellulose acetate butyrate	0 to 40
Plasticizer	20 to 40

Properties Desired:

1. Good adhesion
2. Superior pigment wetting
3. Resistance to water and dilute alkalis
4. Excellent weatherability
5. Good abrasion resistance
6. Toughness over a broad temperature range
7. Low volatility of the plasticizer

Current Recommendations:

1. Santicizer 261
2. Aroclor 6062
3. Aroclor 5442
4. Santicizer 140
5. Santicizer 160

0145058

TYPICAL PHYSICAL PROPERTIES OF AROCLORS AND AROCLOR BLENDS

Property	AROCLORS				AROCLOR BLENDS				
	Aroclor 1221-B	Aroclor 5432	Aroclor 5442	Aroclor 5460	Aroclor 6040	Aroclor 6050	Aroclor 6062	Aroclor 6070	Aroclor 6090
Appearance	Clear, mobile oil	Clear, yellow viscous liquid	Clear, yellow sticky resin	Clear, yellow to amber brittle resin or flakes	Clear, light yellow mobile oil	Clear, light yellow mobile oil	Clear, yellow viscous liquid	Light yellow sticky resin	Light yellow resin
Color, Maximum	100 APHA*	2 NPA* (Molten)	2 NPA* (Molten)	2 NPA* (Molten)	2 NPA*	2 NPA*	2 NPA*	2 NPA*	2 NPA*
Specific Gravity	1.125 - 1.140 (25°/ 15.5° C)	1.280* - 1.300 (90°/ 15.5° C)	1.470 (25°/ 25° C)	1.670 (25°/ 25° C)	1.326* - 1.346 (25°/ 15.5° C)	1.344* - 1.357 (65°/ 15.5° C)	1.407* - 1.427 (65°/ 15.5° C)	1.425* - 1.440 (90°/ 15.5° C)	-
Acidity, Maximum (Mg KOH/Gm)	0.014*	-	.05*	.05*	0.035*	.035*	0.035*	.035*	.035*
Moisture ppm Maximum	-	-	-	-	250*	250*	250*	250*	-
Refractive Index @ 25° C	-	1.658 - 1.660	1.659 - 1.662	1.660 - 1.665	1.6334	1.6390	1.6463	1.6507	1.6580

0145059

TYPICAL PHYSICAL PROPERTIES OF AROCLORS AND AROCLOR BLENDS

Property	AROCLORS				AROCLOR BLENDS				
	Aroclor 1221-B	Aroclor 5432	Aroclor 5442	Aroclor 5460	Aroclor 6040	Aroclor 6050	Aroclor 6062	Aroclor 6070	Aroclor 6090
Viscosity (ASTM D-88)	38 (100° F SUS)	50-60 (210° F SUS)	300-400 (210° F SUS)	-	106-146* (100° F SUS)	110-125* (130° F SUS)	54-64* (210° F SUS)	82-102* (210° F SUS)	-
Flash Point ° F Minimum (Cleveland Open Cup)	260	470° F	477	None to Boiling	260	260	260	260	340
Fire Point ° F Minimum (Cleveland Open Cup)	280	660° F	> 662	None to Boiling	300	310	320	325	550
Softening Point ° C	-	-	46-52*	98-105.5*	-	-	-	-	64-70*

*Monsanto Specification

0145060

LEXOLDMON003653

Toxicity and Safe Handling

Inhalation

At ordinary temperatures, the Aroclor chlorinated polyphenyls have not presented industrial toxicological problems. The hazard of potential toxic exposure varies with their volatility: the lower-chlorinated, more volatile ones present more of a potential problem from the standpoint of both inhalation and skin contact. When Aroclor plasticizers are used at elevated temperatures, engineering controls must be applied, either by the use of closed systems or by effective local-exhaust ventilation together with general workroom exhaust.

Vapor of the liquid Aroclor plasticizers at room temperature should not be breathed in a confined space, and no vapor of any Aroclor evolved at elevated temperatures should be allowed to be dispersed into the general workroom.

Skin Contact

Continuous or repeated skin contact with the Aroclor plasticizers must be avoided by the use of gloves and protective garments, because of the possible occurrence of a condition called chloracne. Although reports of this condition caused by Aroclor are rare, it can be produced by excessive skin contact. If any Aroclor is spilled on the skin, the skin should be washed in the usual manner with a soap solution.

A burn caused by contact with a hot Aroclor should be treated like any ordinary burn. Aroclor plasticizer adhering to the burned area need not be removed immediately, unless treatment of the burn demands it, in which case either soap and water or repeated washings with a vegetable oil are recommended.

DISTRICT SALES OFFICES ALL DIVISIONS

ATLANTA, GEORGIA 30326

Lenox Towers East
3400 Peachtree Rd. N. E. — Suite 1711
Tel. (404) 577-2260

BOSTON, MASSACHUSETTS 02149

Everett Station
Tel. (617) 387-5010

CHICAGO, ILLINOIS

3158 Des Plaines Ave.
Des Plaines, Illinois 60018
Tel. (312) 296-6688

CINCINNATI, OHIO 45206

1501 Madison Road
Tel. (513) 751-6707

CLEVELAND, OHIO 44122

3645 Warrensville Center Rd.
Tel. (216) 391-5400

DETROIT, MICHIGAN 48235

500 Northland Towers East
Tel. (313) 357-0910

HONOLULU, HAWAII 96812

205 Pacific International Bldg.
677 Ala Moana Blvd., P. O. Box 3824
Tel. (808) 512-744

HOUSTON, TEXAS 77002

1300 Main Street
Tel. (713) Capitol 3-4011

LOS ANGELES, CALIFORNIA 90022

6670 E. Flotilla St.
Tel. (213) 723-2492

MINNEAPOLIS, MINNESOTA 55402

912 Northstar Center 110 S. Seventh St.
Tel. (612) 339-4651

NEW YORK, NEW YORK 10017

277 Park Avenue
Tel. (212) 922-4111

PITTSBURGH, PENNSYLVANIA 15222

No. 4 Gateway Center Bldg. Room 534
Tel. (412) 261-2156

ST. LOUIS, MISSOURI 63166

800 N. Lindbergh Blvd.
Tel. (314) Oxford 4-1000

SAN FRANCISCO BAY AREA

2710 Lafayette, Santa Clara, Calif. 95052
Tel. (408) 243-0414

SEATTLE, WASHINGTON 98104

911 Western Avenue
Tel. (206) Main 2-4203

SPRINGFIELD, MASSACHUSETTS 01101

730 Worcester Ave.
Tel. (413) 788-6911

WILMINGTON, DELAWARE 19803

2005 Concord Pike, Fairfax
Tel. (302) Olympia 8-6531

MONSANTO, 800 N. LINDBERGH BLVD., ST. LOUIS, MISSOURI 63166

**Additional District Offices
are maintained by:**

Agricultural Division

LULING, LOUISIANA 70070
P. O. Box 174
Tel. (504) 784-6283

MEMPHIS, TENNESSEE 38113

1023 Riverside Drive
P.O. Box 13248
Tel. (901) Whitehall 7-3151

Textiles Division

AKRON, OHIO 44313
3030 West Market St.
Tel. (216) 836-7941

ATLANTA, GEORGIA 30303

Atlanta Merchandise Mart
240 Peachtree St., N. W.
Tel. (404) 577-2260

CHARLOTTE, NORTH CAROLINA 28202

Wachovia Bank Building
129 West Trade St.
Tel. (704) 376-8871

ENGLEWOOD CLIFFS, N. J. 07831

851 Palisades Ave.
Tel. (201) 588-2151

NEW YORK, NEW YORK

350 Fifth Ave.
Tel. (201) 556-5100

Hydrocarbons & Polymers Division-Lion Oil

EL DORADO, ARKANSAS 71730

Lion Oil Building
Tel. (501) Union 3-3111

JACKSON, MISSISSIPPI 39208

P. O. Box 10837
Westland Station
Tel. (601) 352-3848

LITTLE ROCK, ARKANSAS 72203

1516 West Seventh St.
Tel. (501) Franklin 6-2437

MEMPHIS, TENNESSEE 38113

1023 Riverside Drive
P. O. Box 13248
Tel. (901) Whitehall 7-3151

Organic Chemicals Division (Rubber Industry)

AKRON, OHIO 44311

920 Brown Street
P. O. Box 2307
Tel. (216) Hemlock 4-1921