

51503

* TR 31040

December 4, 1967

Revision #1

TECHNICAL REQUIREMENT

FOR

ASBESTOS - FINE CHRYSOTILE

PLAINTIFF'S
EXHIBIT
WCD-84

Composition

Hydrous Magnesium Silicate

Material Use

Filler

<u>Property</u>	<u>Test Method</u>	<u>Requirement</u>	
		<u>Min.</u>	<u>Max.</u>
Form	Visual	Fibers	
Color	Visual	White	Gray
Specific Gravity	RTV T-26B	2.53	2.59
Moisture, %	RTV T-1	-	0.5
* Magnetic Particles, number per 100 grams Note #1		-	10.0

* Change

Note 1: One hundred grams of material should be spread uniformly over a flat sheet of paper and stroked several times with a bar or horseshoe magnet. Paper "boots" may be used over the pole or poles of the magnet in order to facilitate removal of any adherent magnetic particles for counting. This should also be done over a clean piece of white paper.

Approved Suppliers

Trade Name


Whittaker, Clark, Daniels

1404 Fine Chrysotile 7TF

Rubberoid Co.

Asbestos Floc. 7TF

R. G. Fisher

by 
J. S. Hutnyan



Manager - Process Control