~~January 16, 1975~~
Supersedes Formula C-970
NEW DATED 1/16/75

# CHICAGO, ILLINOIS, PLANT FORMULA
# READY MIX FILLER C-970

DESCRIPTION OF PRODUCT - Filler for Ready Mix joint compound C-971

| FORMULA | Function | RM Spec | Percent | Lbs/Batch |
|---|---|---|---|---|
| *Asbestos 7RF09 | Bulking agent | 9 | 4.25 | 170.00 |
| Dowicil 75 | Fungicide | 193 | .20 | 8.00 |
| Gelvatol 6000 | Adhesive | 162 | 1.00 | 40.00 |
| Gendriv 492S | Water retention aid | 223 | .75 | 30.00 |
| Mica | Anti-cracking agent | 11 | 9.50 | 380.00 |
| Asbestos (SG-210)" | Bulking agent | ± 18 | 1.25 | 50.00 |
| Limestone | Filler | 13 | 83.05 | 3322.00 |
| | | | 100.00 | 4000.00 |

WORKING CONSISTENCY Specifications - Refer to Plant Testing Procedure No. 32.

| Maximum | Minimum | Average |
|---|---|---|
| 57 | 53 | 55 |

WORKING PROPERTIES Specifications - Refer to Plant Testing Procedure No. 33. Filler shall be very heavily bodied and possess fair plasticity. It shall be free of any coarse, gritty, or undispersed particles.

COLOR Specifications - White
Dried compound shall match color of standard sample.

* ASBESTOS TYPE 09 MAY BE SUBSTITUTED, USE AT A LOADING OF 2.75 (110 LBS/BATCH).

NOTE: A wet mix of the filler shall be prepared according to Formula No. C-972 at least twice a day or with every 6th or 7th batch of filler manufactured. This prepared mix shall be tested and shall meet all the specifications required of Ready Mix Joint Compound - Formula No. C-972.

WNG:jg

PLAINTIFF'S EXHIBIT
GP-2275

Lehnert 10.3.01-61

SGP 0018548