MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE Ko-906-D LOT 35750

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
2498	1		T-52	
2496	1		T-11	
	Lump			
STUMP	4981			

TOTAL NET WT. 4994 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

5-22-80

N34579

DUP050104485

35
247

CG 04 CODE KO-906-D PKG. MAY 12 1980

→ 14 35750

EST. WGT. 1377 LBS.

OPEN

OK
AP

TOTAL WEIGHT 5077# (Req.)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KO-906-D (C)	EWK 1/24/78
	DCG 1/26/78
TYPED BY	
rj 3/6/78	

MAKING NOTES

REMARKS

NAME: KROLOR® ORANGE R

NON-BLEEDING

INSTRUCTIONS

VAT	247				
DATE	5/16/80				
TIME	6:30A				
RELEASED BY	G.B				
PRESS	2	22	23	24	
NO. OF CAKES	46	46	46	52	

PRESS with 25 78

WASH TO 2000 OHMS with 135-145°F water

TEST AFTER 3 HOURS

LOAD on 6 cars

SAMPLES 8 oz Jar

DELIVER TO CTL for color

-PRESSING-

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	9am				
CAKES USED	46				
WATER ON	2:30PM				
HRS. WASHED	5				
OHMS	2500				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F

Dry on fast stage only.
Reset every 5 hrs til dry.

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 14

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 4981

SAMPLED BY RELEASED BY

-GRINDING-

MILL 938 HSP 1/8" RP SCREEN 3500 RPM

MAX. TEMP. 170 °F

SAMPLE / WITHOUT MIXING

SAMPLES 1 Env + 1 Pt can

DELIVER TO C T L

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

DATE MIXED

SAMPLED BY RELEASED BY

DUP050104486



DUP050104487