CG 01 CODE YE-698-D PKG ____

LOT MAY -0-81-E1356

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES - APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

## INSTRUCTIONS = PRESSING = RECORD

| | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|
| VAT | | 242 | | | PRESSLOAD | 1ST | 2ND | 3RD | 4TH | 5TH |
| DATE | | 5-14-81 | | | STARTED | 8AM | | | | |
| TIME | | 6:05AM | | | CAKES USED | 54 | | | | |
| RELEASED BY | | | | | WATER ON | 11:30 | | | | |
| PRESS | 2 | 92 | 93 | | HRS. WASHED | 3 | | | | |
| NO.OF CAKES | 54 | 54 | 54 | | OHMS | 2000 | | | | |

PRESS WITH AGITATION
WASH TO 2000 OHMS WITH 35-75 F WATER
TEST AFTER 2 HOURS
LOAD ON 7 CARS

| | | | | | |
|---|---|---|---|---|---|
| HRS. WASHED | | | | | |
| OHMS | | | | | |
| CAKE CONDITION | | | | | |
| NO CARS LOADED | 3+4 | | | | |

EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY BL

## = DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY T.D.S.

NO DRUMS 19
LUMP WGT 5803

## = GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR HIGH AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050095569

1356
12
365

| | |
|---|---|
| 3.20 | + |
| 0.12 | - |
| 3.36 | + |
| 0.12 | - |
| 3.53 | + |
| 0.12 | - |
| 3.35 | + |
| 0.12 | - |
| 3.25 | + |
| 0.12 | - |
| 2.67 | + |
| 0.12 | - |
| 2.99 | + |
| 0.12 | - |
| 3.33 | + |
| 0.12 | - |
| 3.25 | + |
| 0.12 | - |
| 27.85 | |

1356
41
100

| | |
|---|---|
| 27.85 | + |
| 3.46 | + |
| 0.12 | - |
| 3.00 | + |
| 0.12 | - |
| 3.16 | + |
| 0.12 | - |
| 3.25 | + |
| 0.12 | - |
| 3.33 | + |
| 0.12 | - |
| 3.44 | + |
| 0.12 | - |
| 3.00 | + |
| 0.12 | - |
| 3.07 | + |
| 0.12 | - |
| 3.22 | + |
| 0.12 | - |
| 2.45 | + |
| 0.12 | - |
| 58.03 | * |

DUP050095570