

91/ LOT MAY -0-81-E1505

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

ALTERNATE
TYPED BY JMH
MAKING NOTES

JOB NAME: 01YE69BDPR

INSTRUCTIONS

= PRESSING =

RECORD

VAT 241
DATE 5/22/81
TIME 11:45A
RELEASED BY P.N.
PRESS 2 91 92 93
NO. OF CAKES 32 42 32 32
PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

	1ST	2ND	3RD	4TH	5TH
PRESSLOAD					
STARTED	2:24				
CAKES USED	40				
WATER ON	6 PM				
HRS. WASHED	3 1/2				
OHMS	252				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	5				
EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 10
LUMP WGT 3304

= GRINDING =

MILL MIKROATOMIZE SCREEN RPM
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH
AIR FLOW

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1505
41
17

0.00 *

3.76 +
0.12 -
3.11 +
0.12 -
2.98 +
0.12 -
3.64 +
0.12 -
3.40 +
0.12 -
3.21 +
0.12 -
3.54 +
0.12 -
3.58 +
0.12 -
3.52 +
0.12 -
3.50 +
0.12 -
33.04 *