VISCOSITY WORK SHEET

Item 5096-99	P.T. No.	Date 4/10/56
Worker Stanley	Polymer Lucite	Solvent Chloroform
For Cameron	Charge 1329	Temperature 20°C.
Viscometer No. III	Efflux Time 151.9; 151.9	Weight: Gross 3.6054
Viscometer No. 8	Efflux Time 159.4; 159.4	Tare 3.4804
Viscometer No. A	Efflux Time 169.9; 170.0	Net 0.1250 gm/25 ml.

Sample	Flask	Visc. No.	Solution Efflux Times	Rel. Visc.	Inh. Visc. or M.W.	
5146-48G	17	III	193.3; 193.3	1.273	0.48	✓
5146-48H	0	8	203.4; 203.5; 203.6	1.275	0.49	✓
5146-48I	HB	A	215.9; 215.8; 215.9	1.270	0.48	✓
5146-48J	HY	III	192.8; 192.8	1.270	0.48	✓

ch
FOK

PC-1

4/11/56
May

N38911