

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE BT539 LOT 342357

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	5	557	12	

STUMP

TOTAL NET WT. 357 PKG. N–CODE

PROD. SPVR. DATE 2/13 WHSE. OPER. 292

N 31920



N 31920.01

DUP050292795

12/560

CO 40 CODE RT-539-D PKG. ____

→ FEB 4 - 34259

EST. WGT. 486 LBS.

998

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
RT-539-D (N)	EWK 10-25-77
	DCG 10-25-77
TYPED BY	
jlc 11-15-77	

MAKING NOTES

REMARKS

NAME: NAPHTHANIL® RED DARK BLEEDING

INSTRUCTIONS		-PRESSING- RECORD					
VAT	240	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	2-5-80	STARTED	4 ~~3~~				
TIME	4:35 PM	CAKES USED	36				
RELEASED BY	244	WATER ON	12Pm				
PRESS	12	HRS. WASHED	9				
NO. OF CAKES	36	OHMS	5000				
PRESS	WITHOUT AGITATION	HRS. WASHED					
WASH TO	4000 OHMS WITH 35-75°F WATER	OHMS					
TEST AFTER	4 HOURS	HRS. WASHED					
LOAD	ON 3 CARS	OHMS					
		CAKE CONDITION					
		NO. CARS LOADED	3				
		EXPLAIN LOSSES					
SAMPLES							
DELIVER TO		SAMPLED BY		RELEASED BY	A.K.		

O.K.

-DRYING-

DRY 20 HRS AT 180°F	LUMP: / - OK - WET - SALTS - CONTAMINATE
TEST	Color APPEARS DRY
	ADDITIONAL DRYING HOURS REQUIRED
	NO. DRUMS: 5
SAMPLES	NO. CARS PULLED LUMP WGT. 563
DELIVER TO	SAMPLED BY RELEASED BY BLK

-GRINDING-

MILL #5 LSP 1/8" RP SCREEN 1750 RPM	SCREEN RPM
MAX. TEMP. 170 °F	MAX. TEMP. °F
	EXPLAIN LOSSES CO_2 USAGE: 8-8-8
	OXYGEN
SAMPLE WITHOUT MIXING	DATE MIXED 2/11/80
SAMPLES 1 Env	
DELIVER TO CTL	SAMPLED BY RELEASED BY

N 31920.02

DUP050292796



DUP050292797

N 31920.03