

NOTICE: If the film image
is less clear than this
notice, it is due to the
quality of the document
being filmed

46

"Dutch Boy"
**BASIC SILICATE
WHITE LEAD
45X**

A New Pigment Concept



A Product Development of
NATIONAL LEAD COMPANY

00056

NLI 114359

N12240

"Dutch Boy"

BASIC SILICATE WHITE LEAD 45X

BASIC SILICATE WHITE LEAD 45X is a white pigment intended for use in multiple pigment exterior paints in combination with other pigments in a manner similar to white lead, basic lead sulfate, zinc oxide and leaded zinc. In such applications, it is the most economical, durable, active pigment available to the paint manufacturer.

The physical properties and composition of BASIC SILICATE WHITE LEAD 45X are as follows:

Specific Gravity	6.8
Weight per Gallon, lb.	52.3
Oil Absorption, g per 100 g	15
Color	0
Tinting Strength	90
Hiding Power (complete over black and white), sq. ft. per lb.	12
Retained on #325 sieve, %	0.1
Lead Oxide (PbO), %	62.9
Silicon Dioxide (SiO ₂), %	62.9
Sulfur Trioxide (SO ₃), %	6.2

The unique property of this pigment is its low specific gravity. It has the lowest specific gravity of all the active pigments which means that fewer pounds are required for an equivalent amount of pigment particles. For example, 100 pounds of BASIC SILICATE WHITE LEAD 45X is equivalent in volume and in effect to 161 pounds of basic lead sulfate or 159 pounds of basic carbonate white lead. As a result, a combination of BASIC SILICATE WHITE LEAD 45X and lead free zinc oxide costs less than a corresponding leaded zinc oxide.

BASIC SILICATE WHITE LEAD 45X may be used to replace the basic lead sulfate content of multiple pigment paints, whether the basic lead sulfate is present as such or in leaded zinc oxide. It may also replace basic lead carbonate in multiple pigment paints. In all cases, it can be handled in the same manner

00056

NLI 114360

NOTICE: If the film image
is less clear than this
notice, it is due to the
quality of the document
being filmed

46

with comparable results in paint properties and performance characteristics. Its use enables the paint manufacturer to obtain these results more economically.

The general characteristics of BASIC SILICATE WHITE LEAD 45X on exposure are similar to those of other lead pigments. It is similar to basic lead sulfate in some properties, such as cleaning, but it compares closely to basic lead carbonate in durability.

BASIC SILICATE WHITE LEAD 45X is unique. There is no similar pigment now on the market. Lead silicate pigments which are simply compositions of lead silicate in pigment form do not possess low specific gravity or the other advantages exhibited by BASIC SILICATE WHITE LEAD 45X.

00056

NLI 114361