

5/8/70

ELI,

As per our recent discussion + past
Tests, please arrange to run the
following Lab Tests:

1. STD Formulation:

Dicalite	-	54.5%
Lime	-	36.3
Asbestos (M)	-	<u>9.2</u>
		100.0%

2. Test Formula:

Dicalite -	54.5%
Lime -	36.3
* Bleached Sulfite	<u>9.2</u>
	100.0%

* Bleached Sulfite available from Gene Flood
or Jack Eck.

Make Lab gel - Run MOR, Density
+ check Linear Shrinkage + weight Loss

MICH09071

at 1250°f + 1000°f. Save samples
of original + after heat soak. Test for
me.

Thank you.

W.C. Schwingen