

NO. 3-A
PACKAGE TICKET (DO NOT PASTE ONLY)
 CODE Ky. 907 LOT 38251

NET WT./PKG	NO. PKG	PAGE. WGT	LOCATION	PG
<u>2030</u>	<u>1</u>	<u>T-233</u>		
<u>2040</u>	<u>1</u>	<u>T-201</u>		
<u>2000</u>	<u>1</u>	<u>T-133</u>		
<u>LUMP 6027</u>				
TOTAL NET WT. <u>6070</u>		PKG. N-CODE <u>6027</u>		
PROD. BY <u>98H</u>	DATE <u>12/23/80</u>	INSE. OPER.		

N34733

95
262
CG 03 CODE KY-907-D PKG.
→ DEC-16 80 38251
EST. WGT. 1853 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-907-D (F)	FWK 12/12/77
Alternate	DCG 12/14/77

TYPED BY
ri 2/8/77
MAKING NOTES

REMARKS

TOTAL WGT. 6053#

NAME: KROLOR® YELLOW - MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT		262			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		12-17			STARTED	7 PM				
TIME		6:15P			CAKES USED	72				
RELEASED BY		WBC			WATER ON	10A				
PRESS	96	95			HRS. WASHED	6:35				
NO. OF CAKES	72	72			OHMS	2500				
PRESS With		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 135-145°F water			OHMS					
TEST AFTER 3		HOURS			HRS. WASHED					
LOAD on 10 cars					OHMS					
					CAKE CONDITION	8				
					NO. CARS LOADED	8				
					EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO CTL for colorSAMPLED BY *4/7/77* RELEASED BY *W*

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATE

Dry on first stage only.

Re-act on first stage til dry.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 20
LUMP WGT. 6027
RELEASED BY *134*

-GRINDING-

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1PT CAN
DELIVER TO CTLDATE MIXED
SAMPLED BY
RELEASED BY

38251
41
58

0.00 *
3.29 +
0.12 -
3.24 +
0.12 -
3.31 +
0.12 -
3.35 +
0.12 -
3.07 +
0.12 -
3.29 +
0.12 -
3.15 +
0.12 -
3.23 +
0.12 -
3.12 +
0.12 -
3.18 +
0.12 -
3.31 +
0.12 -
3.30 +
0.12 -
3.35 +
0.12 -
3.15 +
0.12 -
3.21 +
0.12 -
3.24 +
0.12 -
3.09 +
0.12 -
3.28 +
0.12 -
2.91 +
0.12 -
1.59 +
0.12 -
60.27 *