

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Ky 787 LOT 34675

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>67</u>	<u>3350</u>		

STUMP

TOTAL NET WT. 3350 PKG. N-CODE 1170

PROD. SPVR. RH DATE 3, 17, 50 WHSE. OPER. _____

N 26294

DUP050093724

CG 03 CODE KY-787-D PKG.
 → MAR-3 34638
 EST. WGT. 1090 990 LBS.

OK
HP

PROCESSING INSTRUCTIONS: BATCH UNIT

23 243	PROCESSES	APPROVED BY
	KY-787-D (R)	FWK 9/22/76
	Alternate	DCG 9/22/76
	TYPED BY	
	NE 2/12/77	
MAKING NOTES		
REMARKS		

Total Wgt. 3490# 3390

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS					- PRESSING -	RECORD				
VAT					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE		3-4-80			STARTED	3:30 AM				
TIME		3:05 A			CAKES USED	46				
RELEASED BY		130			WATER ON	6A				
PRESS	22	23	24	24	HRS. WASHED	9				
NO. OF CAKES	46	46	46	52	OHMS	2500				
PRESS with		AGITATION			HRS. WASHED					
WASH TO 2000		OHMS with 35-75°F water			OHMS					
TEST AFTER 2		HOURS			HRS. WASHED					
LOAD on 6 cars					OHMS					
					CAKE CONDITION	5				
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES 1-8 oz JAR
DELIVER TO ctl for color

SAMPLED BY #4169 RELEASED BY JZ

- DRYING -

Dry 12 hrs at 220°F.
Then Dry 8 hrs at 160°F.

LUMP: - OK - WET - SALTS .. CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3368
RELEASED BY BL-L

- GRINDING -

MILL 039 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 Pt. can
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050093725

N 26294.01

34638
124
51

2.84 +
0.14 -
2.79 +
0.14 -
2.60 +
0.14 -
2.68 +
0.14 -
2.69 +
0.14 -
2.67 +
0.14 -
2.64 +
0.14 -
2.61 +
0.14 -
2.74 +
0.14 -
2.73 +
0.14 -
2.79 +
0.14 -
2.69 +
0.14 -
3.03 +
0.14 -
33.68 *